

## PHYSICAL AND OPTICAL PROPERTIES OF MINERALS

The chemical formula, crystal system, density, hardness, and index of refraction of some common minerals are given in this table. Entries are arranged alphabetically by mineral name. The columns are:

- ❖ **Formula:** Chemical formula for a typical sample of the mineral. Composition often varies considerably with the origin of the sample.
- ❖ **Crystal system:** tricl = triclinic; monocl = monoclinic; orth = orthorhombic; tetr = tetragonal; hex = hexagonal; rhomb = rhombohedral; cub = cubic.
- ❖ **Density:** Typical density in g/cm<sup>3</sup>. Individual samples may vary by a few percent.
- ❖ **Hardness:** On the Mohs' scale (range of 1 to 10, with talc = 1 and diamond = 10).
- ❖ **Index of refraction:** Values are given for the three coordinate axes in the order of least, intermediate, and greatest

index. For cubic crystals there is only a single value. See Reference 1 for details on the axis systems. Variations of several percent, depending on the origin and exact composition of the sample, are common.

### References

1. Deer, W. A., Howie, R. A., and Zussman, J., *An Introduction to the Rock-Forming Minerals*, 2nd Edition, Longman Scientific & Technical, Harlow, Essex, 1992.
2. Carmichael, R. S., *Practical Handbook of Physical Properties of Rocks and Minerals*, CRC Press, Boca Raton, FL, 1989.
3. Donnay, J. D. H., and Ondik, H. M., *Crystal Data Determinative Tables, Third Edition, Volume 2, Inorganic Compounds*, Joint Committee on Powder Diffraction Standards, Swarthmore, PA, 1973.

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Index of refraction		
				$n_a$	$n_b$	$n_c$
Acanthite	Ag <sub>2</sub> S	orth	7.2	2.3		
Actinolite	Ca <sub>2</sub> (Mg,Fe) <sub>5</sub> Si <sub>8</sub> O <sub>22</sub> (OH,F) <sub>2</sub>	monocl	3.23	5.5	1.624	1.655
Aegirine	NaFe(SiO <sub>3</sub> ) <sub>2</sub>	monocl	3.58	6	1.763	1.800
Akermanite	Ca <sub>2</sub> MgSi <sub>2</sub> O <sub>7</sub>	tetr	2.94	5.5	1.632	1.640
Alabandite	MnS	cub	4.0	3.8		
Albite	NaAlSi <sub>3</sub> O <sub>8</sub>	tricl	2.63	6.3	1.527	1.531
Allanite	(Ca,Mn,Ce,La,Y,Th) <sub>2</sub> (Fe,Ti)(Al,Fe)O-OH (Si <sub>2</sub> O <sub>7</sub> )(SiO <sub>4</sub> )	monocl	3.8	5.8	1.75	1.78
Alle montite	SbAs	hex	6.0	3.5		
Almandine	Fe <sub>3</sub> Al <sub>2</sub> Si <sub>3</sub> O <sub>12</sub>	cub	4.32	6.8	1.830	
Altaite	PbTe	cub	8.16	3		
Aluminite	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>2</sub> (OH) <sub>4</sub> ·7H <sub>2</sub> O	monocl	1.74	1.5	1.459	1.464
Alunite	(K,Na)Al <sub>3</sub> (SO <sub>4</sub> ) <sub>2</sub> (OH) <sub>6</sub>	rhomb	2.8	3.8	1.572	1.592
Alunogen	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> ·18H <sub>2</sub> O	monocl	1.69	1.8	1.467	1.47
Amblygonite	(Li,Na)Al(PO <sub>4</sub> )(F,OH)	tricl	3.1	5.8	1.591	1.604
Analcite	NaAlSi <sub>2</sub> O <sub>6</sub> ·H <sub>2</sub> O	cub	2.27	5.5	1.486	
Anatase	TiO <sub>2</sub>	tetr	4.23	5.8	2.488	2.561
Andalusite	Al <sub>2</sub> OSiO <sub>4</sub>	orth	3.15	7.5	1.635	1.639
Andesine	NaAlSi <sub>3</sub> O <sub>8</sub> ·CaAl <sub>2</sub> Si <sub>2</sub> O <sub>8</sub>	tricl	2.67	6.3	1.550	1.553
Andorite	PbAgSb <sub>3</sub> S <sub>6</sub>	rhomb	5.35	3.3		
Andradite	Ca <sub>3</sub> (Fe,Ti) <sub>2</sub> Si <sub>3</sub> O <sub>12</sub>	cub	3.86	6.8	1.887	
Anglesite	PbSO <sub>4</sub>	orth	6.29	2.8	1.877	1.883
Anhydrite	CaSO <sub>4</sub>	orth	2.96	3.5	1.570	1.575
Ankerite	Ca(Fe,Mg,Mn)(CO <sub>3</sub> ) <sub>2</sub>	rhomb	3.0	3.8	1.529	1.720
Anorthite	CaAl <sub>2</sub> Si <sub>3</sub> O <sub>8</sub>	tricl	2.76	6.3	1.577	1.585
Anorthoclase	(Na,K)AlSi <sub>3</sub> O <sub>8</sub>	tricl	2.58	6	1.523	1.528
Anthophyllite	(Mg,Fe) <sub>2</sub> Si <sub>8</sub> O <sub>22</sub> (OH,F) <sub>2</sub>	rhomb	3.21	5.8	1.645	1.658
Apatite	Ca <sub>5</sub> (PO <sub>4</sub> ) <sub>3</sub> (OH,F,Cl)	hex	3.2	5	1.645	1.648
Apophyllite	KFCa <sub>4</sub> Si <sub>8</sub> O <sub>20</sub> ·8H <sub>2</sub> O	tetr	2.35	4.8	1.535	1.536
Aragonite	CaCO <sub>3</sub>	orth	2.83	3.5	1.531	1.680
Arcanite	K <sub>2</sub> SO <sub>4</sub>	orth	2.66		1.494	1.494
Argentite	Ag <sub>2</sub> S	orth	7.2	2.3		
Arsenolite	As <sub>2</sub> O <sub>3</sub>	cub	3.86	1.5	1.755	
Arsenopyrite	FeAsS	monocl	6.1	5.8		
Atacamite	Cu <sub>2</sub> (OH) <sub>3</sub> Cl	rhomb	3.76	3.3	1.831	1.861
Augelite	Al <sub>2</sub> (PO <sub>4</sub> ) <sub>2</sub> (OH) <sub>3</sub>	monocl	2.70	4.8	1.574	1.576
Augite	(Ca,Mg,Fe,Ti,Al) <sub>2</sub> (Si,Al) <sub>2</sub> O <sub>6</sub>	monocl	3.38	6	1.703	1.707
Autunite	Ca(UO <sub>2</sub> ) <sub>2</sub> (PO <sub>4</sub> ) <sub>2</sub> ·10H <sub>2</sub> O	tetr	3.2	2.3	1.553	1.577
Axinite	(Ca,Mn,Fe) <sub>3</sub> Al <sub>2</sub> BO <sub>3</sub> Si <sub>4</sub> O <sub>12</sub> (OH)	tricl	3.31	6.8	1.684	1.691

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					<i>n</i> <sub>α</sub>	<i>n</i> <sub>β</sub>	<i>n</i> <sub>γ</sub>
Azurite	Cu <sub>3</sub> (OH) <sub>2</sub> (CO <sub>3</sub> ) <sub>2</sub>	monocl	3.77	3.8	1.730	1.758	1.838
Baddeleyite	ZrO <sub>2</sub>	monocl	5.7	6.5	2.13	2.19	2.20
Barite	BaSO <sub>4</sub>	orth	4.49	3.3	1.636	1.637	1.648
Benitoite	BaTi(SiO <sub>3</sub> ) <sub>3</sub>	rhomb	3.65	6.3	1.757	1.804	
Bertrandite	Be <sub>4</sub> Si <sub>2</sub> O <sub>7</sub> (OH) <sub>2</sub>	rhomb	2.6	6	1.589	1.602	1.613
Beryl	Be <sub>3</sub> Al <sub>2</sub> (SiO <sub>3</sub> ) <sub>6</sub>	hex	2.64	7.8	1.582	1.589	
Beryllonite	NaBe(PO) <sub>4</sub>	monocl	2.81	5.8	1.552	1.558	1.561
Biotite	K(Mg,Fe) <sub>3</sub> AlSi <sub>3</sub> O <sub>10</sub> (OH,F) <sub>2</sub>	monocl	3.0	2.8	1.595	1.651	1.651
Bismuthinite	Bi <sub>2</sub> S <sub>3</sub>	orth	6.78	2			
Bixbyite	(Mn,Fe) <sub>2</sub> O <sub>3</sub>	cub	4.95	6.3			
Bloedite	Na <sub>2</sub> Mg(SO <sub>4</sub> ) <sub>2</sub> ·4H <sub>2</sub> O	monocl	2.25	2.8	1.483	1.486	1.487
Boehmite	AlO(OH)	orth	3.44	3.8	1.64	1.65	1.66
Boracite	Mg <sub>3</sub> B <sub>7</sub> O <sub>13</sub> Cl	rhomb	2.94	7.3	1.66	1.66	1.67
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> ·10H <sub>2</sub> O	monocl	1.73	2.3	1.447	1.469	1.472
Bornite	Cu <sub>5</sub> FeS <sub>4</sub>	cub	5.07	3			
Boulangerite	Pb <sub>5</sub> Sb <sub>4</sub> S <sub>11</sub>	monocl	6.1	2.8			
Bournonite	PbCuSbS <sub>3</sub>	rhomb	5.83	2.8			
Braggite	PtS	tetr	10.2				
Braunite	(Mn,Si) <sub>2</sub> O <sub>3</sub>	tetr	4.78	6.3			
Bravoite	(Ni,Fe)S <sub>2</sub>	cub	4.62	5.8			
Breithauptite	NiSb	hex	≈8.7	5.5			
Brochantite	Cu <sub>3</sub> (SO <sub>4</sub> )(OH) <sub>6</sub>	monocl	3.79	3.8	1.728	1.771	1.800
Bromyrite	AgBr	cub	6.47	2.5	2.253		
Brookite	TiO <sub>2</sub>	orth	4.23	5.8	2.583	2.584	2.700
Brucite	Mg(OH) <sub>2</sub>	hex	2.37	2.5	1.575	1.59	
Bunsenite	NiO	cub	6.72	5.5			
Cacoxenite	Fe <sub>4</sub> (PO <sub>4</sub> ) <sub>3</sub> (OH) <sub>3</sub> ·12H <sub>2</sub> O	hex	2.3	3.5	1.580	1.646	
Calcite	CaCO <sub>3</sub>	hex	2.71	3	1.486	1.658	
Caledonite	Cu <sub>2</sub> Pb <sub>5</sub> (SO <sub>4</sub> ) <sub>3</sub> (CO <sub>3</sub> )(OH) <sub>6</sub>	rhomb	5.76	2.8	1.818	1.866	1.909
Calomel	Hg <sub>2</sub> Cl <sub>2</sub>	tetr	7.16	1.5	1.973	2.656	
Cancrinite	(Na,Ca,K) <sub>7</sub> [Al <sub>6</sub> Si <sub>6</sub> O <sub>24</sub> ](CO <sub>3</sub> ,SO <sub>4</sub> ,Cl,OH) <sub>2</sub> ·H <sub>2</sub> O	hex	2.42	5.5	1.495	1.509	
Carnalite	KMgCl <sub>3</sub> ·6H <sub>2</sub> O	rhomb	1.60	2.5	1.466	1.475	1.494
Carnotite	K <sub>2</sub> (UO <sub>2</sub> ) <sub>2</sub> (VO <sub>4</sub> ) <sub>2</sub> ·3H <sub>2</sub> O	rhomb		1.5	1.75	1.92	1.95
Cassiterite	SnO <sub>2</sub>	tetr	6.85	6.5	2.006	2.097	
Celestite	SrSO <sub>4</sub>	orth	3.96	3.3	1.622	1.624	1.631
Celsian	BaAl <sub>2</sub> Si <sub>2</sub> O <sub>8</sub>	monocl	3.25	6.3	1.583	1.588	1.594
Cerargyrite	AgCl	cub	5.56	2.5	2.071		
Cerussite	PbCO <sub>3</sub>	orth	6.6	3.3	1.804	2.076	2.079
Cervantite	Sb <sub>2</sub> O <sub>4</sub>	orth	6.64	4.5			
Chabazite	Ca[Al <sub>2</sub> Si <sub>4</sub> O <sub>12</sub> ]·6H <sub>2</sub> O	trig	2.08	4.5	1.482		
Chalcanthite	CuSO <sub>4</sub> ·5H <sub>2</sub> O	tricl	2.29	2.5	1.514	1.537	1.543
Chalcocite	Cu <sub>2</sub> S	orth	5.6	2.8			
Chalcopyrite	CuFeS <sub>2</sub>	tetr	4.2	3.8			
Chiolite	Na <sub>5</sub> Al <sub>3</sub> F <sub>14</sub>	tetr	3.00	3.8	1.342	1.349	
Chlorite	(Mg,Al,Fe) <sub>12</sub> (Si,Al) <sub>8</sub> O <sub>20</sub> (OH) <sub>16</sub>	monocl	3.0	2.5	1.61	1.62	1.62
Chloritoid	FeAl <sub>2</sub> O <sub>2</sub> (SiO <sub>4</sub> ) <sub>2</sub> (OH) <sub>4</sub>	monocl	3.66	6.5	1.717	1.721	1.726
Chondrodite	Mg(OH,F) <sub>2</sub> ·2Mg <sub>2</sub> SiO <sub>4</sub>	monocl	3.21	6.5	1.604	1.615	1.634
Chromite	FeCr <sub>2</sub> O <sub>4</sub>	cub	5.0	5.5	2.16		
Chrysoberyl	BeAl <sub>2</sub> O <sub>4</sub>	orth	3.65	8.5	1.746	1.748	1.756
Chrysocolla	CuSiO <sub>3</sub> ·2H <sub>2</sub> O	rhomb	2.4	2	1.575	1.597	1.598
Cinnabar	HgS	hex	8.17	2.3	2.814	3.143	
Claudetite	As <sub>2</sub> O <sub>3</sub>	monocl	3.74	2.5	1.87	1.92	2.01
Clinohumite	Mg(OH,F) <sub>2</sub> ·4Mg <sub>2</sub> SiO <sub>4</sub>	monocl	3.21	6	1.633	1.647	1.668
Clinozoisite	Ca <sub>2</sub> Al <sub>3</sub> Si <sub>3</sub> O <sub>12</sub> (OH)	monocl	3.30	6.5	1.693	1.700	1.712
Cobaltite	CoAsS	cub	≈6.1	5.5			
Colemanite	Ca <sub>8</sub> B <sub>6</sub> O <sub>11</sub> ·5H <sub>2</sub> O	monocl	2.42	4.5	1.586	1.592	1.614
Columbite	(Fe,Mn)(Nb,Ta) <sub>2</sub> O <sub>6</sub>	rhomb	5.20	6			
Connellite	Cu <sub>19</sub> (SO <sub>4</sub> )Cl <sub>4</sub> (OH) <sub>32</sub> ·3H <sub>2</sub> O	hex	3.36	3	1.731	1.752	
Copiapite	(Fe,Mg)Fe <sub>4</sub> (SO <sub>4</sub> ) <sub>6</sub> (OH) <sub>2</sub> ·20H <sub>2</sub> O	tricl	2.13	2.8	1.52	1.54	1.59
Coquimbite	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> ·9H <sub>2</sub> O	hex	2.1	2.5	1.54	1.56	

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					<i>n</i> <sub>α</sub>	<i>n</i> <sub>β</sub>	<i>n</i> <sub>γ</sub>
Cordierite	$\text{Al}_3(\text{Mg},\text{Fe})_2\text{Si}_5\text{AlO}_{18}$	rhomb	2.66	7	1.540	1.549	1.553
Corundum	$\text{Al}_2\text{O}_3$	hex	3.97	9	1.761	1.769	
Cotunnite	$\text{PbCl}_2$	orth	5.98	2.5	2.199	2.217	2.260
Covellite	$\text{CuS}$	hex	4.8	1.8			
Cristobalite	$\text{SiO}_2$	hex	2.33	6.5	1.484	1.487	
Crocoite	$\text{PbCrO}_4$	monocl	6.12	2.8	2.29	2.36	2.66
Cryolite	$\text{Na}_3\text{AlF}_6$	monocl	2.97	2.5	1.338	1.338	1.339
Cryolithionite	$\text{Na}_3\text{Li}_3\text{Al}_2\text{F}_{12}$	cub	2.77	2.8	1.340		
Cubanite	$\text{CuFe}_2\text{S}_3$	rhomb	4.11	3.5			
Cummingtonite	$(\text{Mg},\text{Fe})_7\text{Si}_8\text{O}_{22}(\text{OH})_2$	monocl	3.4	5.5	1.650	1.660	1.676
Cuprite	$\text{Cu}_2\text{O}$	cub	6.0	3.8			
Danburite	$\text{CaSi}_2\text{B}_2\text{O}_8$	rhomb	3.0	7	1.63	1.63	1.63
Datolite	$\text{CaBSiO}_4(\text{OH})$	monocl	2.98	5.3	1.624	1.652	1.668
Daubreelite	$\text{Cr}_2\text{FeS}_4$	cub	3.81				
Derbylite	$\text{Fe}_6\text{Ti}_6\text{Sb}_2\text{O}_{23}$	rhomb	4.53	5	2.45	2.45	2.51
Diamond	C	cub	3.51	10	2.418		
Diaspore	$\text{AlO}(\text{OH})$	orth	3.4	6.8	1.694	1.715	1.741
Digenite	$\text{Cu}_{2-x}\text{S}$	cub	5.55	2.8			
Diopside	$\text{CaMgSi}_2\text{O}_6$	monocl	3.30	6	1.680	1.687	1.708
Diophtase	$\text{CuSiO}_2(\text{OH})_2$	rhomb	3.5	5	1.65	1.70	
Dolomite	$\text{CaMg}(\text{CO}_3)_2$	rhomb	2.86	3.5	1.500	1.679	
Douglasite	$\text{K}_2\text{FeCl}_4 \cdot 2\text{H}_2\text{O}$	orth	2.16		1.488	1.500	
Dyscrasite	$\text{Ag}_2\text{Sb}$	rhomb	9.74	3.8			
Eddingtonite	$\text{BaAl}_2\text{Si}_3\text{O}_{10} \cdot 4\text{H}_2\text{O}$	rhomb	2.8		1.541	1.553	1.557
Eglestonite	$\text{Hg}_2\text{OCl}_2$	cub	8.4	2.5	2.49		
Emplectite	$\text{CuBiS}_2$	rhomb	6.38	2			
Enargite	$\text{Cu}_3\text{AsS}_4$	rhomb	4.5	3			
Enstatite	$\text{MgSiO}_3$	monocl	3.19	5.5	1.656	1.662	1.669
Epidote	$\text{Ca}_2\text{Al}_2(\text{Al},\text{Fe})\text{OH}(\text{SiO}_4)_3$	monocl	3.44	6	1.733	1.755	1.765
Epsomite	$\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$	orth	1.67	2.3	1.433	1.455	1.461
Erythrite	$(\text{Co},\text{Ni})_3(\text{AsO}_4)_2 \cdot 8\text{H}_2\text{O}$	monocl	3.06	2	1.626	1.661	1.699
Eucairite	$\text{CuAgSe}$	orth	7.7	2.5			
Euclasite	$\text{BeAlSiO}_4(\text{OH})$	monocl	3.1	7.5	1.651	1.655	1.671
Eudialite	$(\text{Na},\text{Ca},\text{Ce})_5(\text{Fe},\text{Mn})(\text{Zr},\text{Ti})(\text{Si}_3\text{O}_9)_2(\text{OH},\text{Cl})$	hex	3.0	5.5	1.623	1.600	1.615
Eulytite	$\text{Bi}_4\text{Si}_3\text{O}_{12}$	cub	6.6	4.5	2.05		
Euxenite	$(\text{Y},\text{Ca},\text{Ce},\text{U},\text{Th})(\text{Nb},\text{Ta},\text{Ti})_2\text{O}_6$	rhomb	5.5	6	2.2		
Fayalite	$\text{Fe}_2\text{SiO}_4$	orth	4.30	6.5	1.827	1.869	1.879
Ferberite	$\text{FeWO}_4$	monocl	7.51	4.3			
Fergussonite	$(\text{Y},\text{Er},\text{Ce},\text{Fe})(\text{Nb},\text{Ta},\text{Ti})\text{O}_4$	tetr	5.7	6	2.1		
Fluorite	$\text{CaF}_2$	cub	3.18	4	1.434		
Forsterite	$\text{Mg}_2\text{SiO}_4$	orth	3.21	7	1.635	1.651	1.670
Franklinite	$\text{ZnFe}_2\text{O}_4$	cub	5.21	6	2.36		
Gahnite	$\text{ZnAl}_2\text{O}_4$	cub	4.62	7.8	1.805		
Galaxite	$\text{MnAl}_2\text{O}_4$	cub	4.04	7.8	1.92		
Galena	PbS	cub	7.60	2.5	3.91		
Galenabismuthite	$\text{PbBi}_2\text{S}_4$	rhomb	7.04	3			
Ganomalite	$(\text{Ca},\text{Pb})_{10}(\text{OH},\text{Cl})_2(\text{Si}_2\text{O}_7)_3$	hex	5.6	3.5	1.910	1.945	
Gaylussite	$\text{Na}_2\text{Ca}(\text{CO}_3)_2 \cdot 5\text{H}_2\text{O}$	monocl	1.99	2.8	1.444	1.516	1.523
Gehlenite	$\text{Ca}_2\text{Al}_2\text{SiO}_7$	tetr	3.04	5.5	1.658	1.669	
Geikielite	$\text{MgTiO}_3$	hex	3.85	5.5	1.95	2.31	
Gibbsite	$\text{Al}(\text{OH})_3$	monocl	2.42	3	1.57	1.57	1.59
Glauberite	$\text{Na}_2\text{Ca}(\text{SO}_4)_2$	monocl	2.80	2.8	1.515	1.535	1.536
Glauconite	$(\text{K},\text{Na},\text{Ca})_{1-6}(\text{Fe},\text{Al},\text{Mg})_{4-6}\text{Si}_{7-3}\text{Al}_{0-7}\text{O}_{20}(\text{OH})_4$	monocl	2.7	2	1.60	1.63	1.63
Glauconophane	$\text{Na}_2\text{Mg}_3\text{Al}_2\text{Si}_8\text{O}_{22}(\text{OH})_2$	monocl	3.19	6	1.634	1.645	1.648
Gmelinite	$(\text{Ca},\text{Na}_2)[\text{Al}_2\text{Si}_4\text{O}_{12}] \cdot 6\text{H}_2\text{O}$	hex	2.10	4.5	1.477	1.485	
Goethite	$\text{FeO}(\text{OH})$	orth	4.3	5.3	2.268	2.401	2.457
Goslarite	$\text{ZnSO}_4 \cdot 7\text{H}_2\text{O}$	orth	1.97	2.3	1.457	1.480	1.484
Greenockite	CdS	hex	4.8	3.3	2.506	2.529	
Grossularite	$\text{Ca}_3\text{Al}_2\text{Si}_3\text{O}_{12}$	cub	3.59	6.8	1.734		
Gummite	$\text{UO}_3 \cdot \text{H}_2\text{O}$	orth	7.05	3.8			

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					<i>n</i> <sub>α</sub>	<i>n</i> <sub>β</sub>	<i>n</i> <sub>γ</sub>
Gypsum	CaSO <sub>4</sub> ·2H <sub>2</sub> O	monocl	2.32	2	1.520	1.525	1.530
Halite	NaCl	cub	2.17	2	1.544		
Hambergerite	Be <sub>2</sub> (OH)(BO <sub>3</sub> )	rhomb	2.36	7.5	1.56	1.59	1.63
Hanksite	Na <sub>22</sub> K(SO <sub>4</sub> ) <sub>9</sub> (CO <sub>3</sub> ) <sub>2</sub> Cl	hex	2.56	3.3	1.461	1.481	
Harmotome	Ba[Al <sub>2</sub> Si <sub>6</sub> O <sub>16</sub> ]·6H <sub>2</sub> O	monocl	2.44	4.5	1.506	1.507	1.511
Hausmannite	Mn <sub>3</sub> O <sub>4</sub>	tetr	4.84	5.5	2.15	2.46	
Haüyne	(Na,Ca) <sub>4.8</sub> Al <sub>6</sub> Si <sub>6</sub> O <sub>24</sub> (SO <sub>4</sub> ) <sub>2</sub>	cub	2.47	5.8	1.502		
Hedenbergite	CaFeSi <sub>2</sub> O <sub>6</sub>	monocl	3.53	6	1.721	1.727	1.746
Helvitite	Mn <sub>4</sub> Be <sub>3</sub> Si <sub>3</sub> O <sub>12</sub> S	cub	3.32	6	1.739		
Hematite	Fe <sub>2</sub> O <sub>3</sub>	hex	5.25	6	2.91	3.19	
Hemimorphite	Zn <sub>4</sub> Si <sub>2</sub> O <sub>7</sub> (OH) <sub>2</sub> ·H <sub>2</sub> O	rhomb	3.45	5	1.614	1.617	1.636
Hercynite	Fe(AlO <sub>2</sub> ) <sub>2</sub>	cub	4.3	7.8	1.835		
Herderite	CaBe(PO <sub>4</sub> )(Fe,OH)	monocl	2.98	5.3	1.592	1.612	1.621
Hessite	Ag <sub>2</sub> Te	orth	8.4	2.5			
Heulandite	(Ca,Na <sub>2</sub> K <sub>2</sub> )[Al <sub>2</sub> Si <sub>7</sub> O <sub>18</sub> ]·6H <sub>2</sub> O	monocl	2.2	3.8	1.498	1.498	1.506
Hopeite	Zn <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub> ·4H <sub>2</sub> O	orth	3.0	3.2	1.58	1.59	1.59
Hornblende	Ca <sub>2</sub> (Mg,Fe) <sub>4</sub> Al(Si <sub>7</sub> AlO <sub>22</sub> )(OH) <sub>2</sub>	monocl	3.24	5.5	1.67	1.67	1.69
Huebnerite	MnWO <sub>4</sub>	monocl	7.2	4.3	2.17	2.22	2.32
Humite	Mg(OH,F) <sub>2</sub> ·3Mg <sub>2</sub> SiO <sub>4</sub>	orth	3.3	6	1.625	1.636	1.657
Huntite	Mg <sub>3</sub> Ca(CO <sub>3</sub> ) <sub>4</sub>	trig	2.70				
Hydrogrossularite	Ca <sub>3</sub> Al <sub>2</sub> Si <sub>2</sub> O <sub>8</sub> (SiO <sub>4</sub> ) <sub>1-m</sub> (OH) <sub>4m</sub>	cub	3.4	6.8	1.70		
Hydromagnesite	3MgCO <sub>3</sub> ·Mg(OH) <sub>2</sub> ·3H <sub>2</sub> O	monocl	2.24	3.5	1.523	1.527	1.545
Illite	KAl <sub>4</sub> [Si <sub>7</sub> AlO <sub>20</sub> ](OH) <sub>4</sub>	monocl	2.8	1.5	1.56	1.59	1.59
Ilmenite	FeTiO <sub>3</sub>	rhomb	4.72	5.5			
Iodyrite	AgI	hex	5.68	1.5	2.21	2.22	
Jacobsite	MnFe <sub>2</sub> O <sub>4</sub>	cub	4.87	7.8	2.3		
Jadeite	NaAlSi <sub>2</sub> O <sub>6</sub>	monocl	3.34	6	1.649	1.654	1.663
Jamesonite	Pb <sub>4</sub> FeSb <sub>6</sub> S <sub>14</sub>	monocl	5.63	2.5			
Jarosite	KFe <sub>3</sub> (SO <sub>4</sub> ) <sub>2</sub> (OH) <sub>6</sub>	rhomb	3.09	3	1.715	1.820	
Kainite	KMg(SO <sub>4</sub> )Cl·3H <sub>2</sub> O	monocl	2.15	2.8	1.494	1.505	1.516
Kaliophylite	KAlSiO <sub>4</sub>	hex	2.61	6	1.532	1.537	
Kaolinite	Al <sub>4</sub> Si <sub>4</sub> O <sub>10</sub> (OH) <sub>8</sub>	tricl	2.65	2.3	1.549	1.564	1.565
Kernite	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> ·4H <sub>2</sub> O	monocl	1.95	2.5	1.454	1.472	1.488
Kieserite	MgSO <sub>4</sub> ·H <sub>2</sub> O	monocl	2.57	3.5	1.520	1.533	1.584
Kyanite	Al <sub>2</sub> OSiO <sub>4</sub>	tricl	3.59	6.3	1.715	1.722	1.731
Lanarkite	Pb <sub>2</sub> (SO <sub>4</sub> )O	monocl	6.92	2.3	1.928	2.007	2.036
Lanthanite	(La,Ce) <sub>2</sub> (CO <sub>3</sub> ) <sub>3</sub> ·8H <sub>2</sub> O	rhomb	2.72	2.8	1.52	1.587	1.613
Laumontite	Ca <sub>4</sub> [Al <sub>8</sub> Si <sub>16</sub> O <sub>48</sub> ]·16H <sub>2</sub> O	monocl	2.3	3.3	1.508	1.517	1.519
Laurionite	Pb(OH)Cl	rhomb	6.24	3.3	2.08	2.12	2.16
Lawsonite	CaAl <sub>2</sub> (OH) <sub>5</sub> Si <sub>2</sub> O <sub>7</sub> ·H <sub>2</sub> O	rhomb	3.08	6	1.655	1.675	1.685
Lazulite	(Mg,Fe)Al <sub>2</sub> (PO <sub>4</sub> ) <sub>2</sub> (OH) <sub>2</sub>	monocl	3.23	5.8	1.615	1.64	1.650
Lazurite	Na <sub>4</sub> SSi <sub>3</sub> Al <sub>3</sub> O <sub>12</sub>	cub	2.42	5.3	1.500		
Leadhillite	Pb <sub>4</sub> (SO <sub>4</sub> )(CO <sub>3</sub> ) <sub>2</sub> (OH) <sub>2</sub>	monocl	6.55	2.8	1.87	2.00	2.01
Lepidocrocite	FeO(OH)	orth	4.26	5	1.94	2.20	2.51
Lepidolite	K <sub>2</sub> (Li,Al) <sub>5-6</sub> [Si <sub>6-7</sub> Al <sub>2-1</sub> O <sub>20</sub> ](OH,F) <sub>4</sub>	monocl	2.85	3.3	1.536	1.565	1.566
Leucite	KAlSi <sub>2</sub> O <sub>6</sub>	tetr	2.49	5.8	1.510		
Levyne	(Ca,Na <sub>2</sub> )Al <sub>2</sub> Si <sub>4</sub> O <sub>12</sub> ·6H <sub>2</sub> O	rhomb	2.10	4.5	1.496	1.501	
Litharge	PbO	tetr	9.35	2	2.535	2.665	
Loellingite	FeAs <sub>2</sub>	rhomb	7.40	5.3			
Maghemite	Fe <sub>2</sub> O <sub>3</sub>	cub	4.88	7.8	2.63		
Magnesite	MgCO <sub>3</sub>	hex	3.05	4	1.536	1.741	
Magnetite	Fe <sub>3</sub> O <sub>4</sub>	cub	5.17	6	2.42		
Malachite	Cu <sub>2</sub> (OH) <sub>2</sub> (CO <sub>3</sub> )	monocl	4.05	3.8	1.655	1.875	1.909
Manganite	MnO(OH)	monocl	≈4.3	4	2.25	2.25	2.53
Manganosite	MnO	cub	5.37	5.5			
Marcasite	FeS <sub>2</sub>	cub	5.02	6.3			
Marialite	Na <sub>4</sub> Al <sub>3</sub> Si <sub>9</sub> O <sub>24</sub> Cl	tetr	2.56	5.5	1.541	1.548	
Marshite	CuI	cub	5.67	2.5	2.346		
Mascagnite	(NH <sub>4</sub> ) <sub>2</sub> SO <sub>4</sub>	orth	1.77	2.3	1.520	1.523	1.533
Matlockite	PbClF	tetr	7.05	2.8	2.006	2.145	

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					<i>n</i> <sub>α</sub>	<i>n</i> <sub>β</sub>	<i>n</i> <sub>γ</sub>
Meionite	<chem>Ca4Al6Si6O24CO3</chem>	tetr	2.78	5.5	1.559	1.595	
Melanterite	<chem>FeSO4·7H2O</chem>	monocl	1.89	2	1.47	1.48	1.49
Melilite	<chem>(Ca,Na)2(Mg,Fe,Al,Si)3O7</chem>	tetr	3.00	5.5	1.639	1.645	
Mellite	<chem>Al2C12O12·18H2O</chem>	tetr	1.64	2.3	1.511	1.539	
Mendipite	<chem>Pb3O2Cl2</chem>	rhomb	7.24	2.5	2.24	2.27	2.31
Mesolite	<chem>Na2Ca2(Al2Si3O10)3·8H2O</chem>	orth	2.26	5	1.506		
Metacinnabar	HgS	cub	7.70	3			
Microcline	<chem>KAlSi3O8</chem>	monocl	2.56	6.3	1.522	1.526	1.530
Miersite	AgI	hex	5.68	2.5	2.20		
Millerite	NiS	hex	5.5	3.3			
Mimetite	<chem>Pb5(AsO4)3Cl</chem>	hex	7.24	3.8	2.128	2.147	
Minium	<chem>Pb3O4</chem>	tetr	8.9	2.5			
Mirabilite	<chem>Na2SO4·10H2O</chem>	monocl	1.46	1.8	1.394	1.396	1.398
Moissanite	SiC	hex	3.16	9.5	2.648	2.691	
Molybdenite	MoS <sub>2</sub>	hex	5.06	1.3			
Monazite	<chem>(Ce,La,Th)PO4</chem>	monocl	5.2	5	1.787	1.789	1.840
Monetite	CaHPO <sub>4</sub>	tricl	2.92	3.5	1.587	1.61	1.640
Monticellite	<chem>Ca(Mg,Fe)SiO4</chem>	orth	3.18	5.5	1.647	1.655	1.664
Montmorillonite	<chem>(0.5Ca,Na)0.7(Al,Mg,Fe)4[(Si,Al)8O20](OH)4·nH2O</chem>	monocl	2.5	1.5	1.55	1.57	1.57
Montroydite	HgO	orth	11.14	2.5	2.37	2.50	2.65
Mordenite	<chem>(Na,K,Ca)[Al2Si10O24]·7H2O</chem>	orth	2.13	3.5	1.478	1.480	1.482
Muscovite	<chem>KAl2Si3AlO10(OH,F)2</chem>	monocl	2.83	2.8	1.563	1.596	1.602
Nantokite	CuCl	cub	4.14	2.5	1.930		
Natrolite	<chem>Na2Al2Si3O10·2H2O</chem>	orth	2.23	5	1.478	1.481	1.491
Nepheline	<chem>Na3KAl4Si4O16</chem>	hex	2.61	5.8	1.534	1.538	
Newberryite	<chem>MgHPO4·3H2O</chem>	orth	2.13	3.3	1.514	1.517	1.533
Niccolite	NiAs	hex	7.77	5.3			
Norbergite	<chem>Mg(OH,F)2·Mg2SiO4</chem>	orth	3.21	6.5	1.565	1.573	1.592
Nosean	<chem>Na8Al6Si6O24SO4</chem>	cub	2.35	5.5	1.495		
Oldhamite	CaS	cub	2.59	4	2.137		
Oligoclase	<chem>([NaSi]0.9·0.7[CaAl]0.1·0.3)AlSi2O8</chem>	tricl	2.64	6.3	1.539	1.543	1.547
Oliveneite	<chem>Cu2(AsO4)·(OH)</chem>	rhomb	4.2	3	1.77	1.80	1.85
Olivine	<chem>(Mg,Fe)SiO4</chem>	rhomb	3.81	6.8	1.73	1.76	1.78
Opal	<chem>SiO2·nH2O</chem>	amorp	1.9	5	1.44		
Orpiment	As <sub>2</sub> S <sub>3</sub>	monocl	3.46	1.8	2.40	2.81	3.02
Orthoclase	<chem>KAlSi3O8</chem>	monocl	2.56	6	1.523	1.527	1.531
Orthopyroxene	<chem>(Mg,Fe)SiO3</chem>	rhomb	3.6	5.5	1.709	1.712	1.723
Paragonite	<chem>NaAl2Si3AlO10(OH)2</chem>	monocl	2.85	2.5	1.572	1.602	1.605
Parisite	<chem>(Ce,La,Na)FCO3·CaCO3</chem>	hex	4.42	4.5	1.672	1.771	
Pectolite	<chem>Ca3NaH(SiO3)3</chem>	tricl	2.88	4.8	1.603	1.610	1.639
Penfieldite	<chem>Pb2Cl6(OH)2</chem>	hex	6.6		2.13	2.21	
Pentlandite	<chem>(Fe,Ni)9S8</chem>	cub	4.8	3.8			
Percyelite	<chem>PbCuCl2(OH)2</chem>	cub		2.5	2.05		
Periclaste	MgO	cub	3.6	5.5	1.735		
Perovskite	CaTiO <sub>3</sub>	cub	3.98	5.5	2.34		
Petalite	LiAlSi <sub>4</sub> O <sub>10</sub>	monocl	2.42	6.5	1.506	1.511	1.519
Pharmacosiderite	<chem>Fe3(AsO4)2(OH)3·5H2O</chem>	cub	2.80	2.5	1.690		
Phenakite	Be <sub>2</sub> SiO <sub>4</sub>	rhomb	2.98	7.5	1.654	1.670	
Phillipsite	<chem>K(Ca0.5·Na)2[Al3Si5O16]·6H2O</chem>	monocl	2.2	4.3	1.494	1.497	1.505
Phlogopite	<chem>KMg3AlSi3O10(OH,F)2</chem>	monocl	2.83	2.3	1.560	1.597	1.598
Phosgenite	<chem>Pb2(CO3)Cl2</chem>	tetr	6.13	2.5	2.118	2.145	
Piemontite	<chem>Ca2(Mn,Fe,Al)3O(Si2O7)(SiO4)(OH)</chem>	monocl	3.49	6	1.762	1.773	1.796
Pigeonite	<chem>(Mg,Fe,Ca)(Mg,Fe)Si2O6</chem>	monocl	3.38	6	1.702	1.703	1.728
Pollucite	<chem>CsAlSi2O6</chem>	tetr	2.9	6.5	1.517		
Polybasite	<chem>(Ag,Cu)16Sb2S11</chem>	monocl	6.1	2.5			
Powellite	<chem>Ca(Mo,W)O4</chem>	tetr	4.35	3.8	1.971	1.980	
Prehnite	<chem>Ca2Al2Si3O10(OH)2</chem>	rhomb	2.93	6.3	1.622	1.628	1.648
Proustite	Ag <sub>3</sub> AsS <sub>3</sub>	rhomb	5.57	2.3	2.792	3.088	
Pseudobrookite	<chem>Fe2TiO5</chem>	rhomb	4.36	6	2.38	2.39	2.42
Psilomelane	<chem>BaMn9O16(OH)4</chem>	rhomb	4.71	5.5			

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					$n_{\alpha}$	$n_{\beta}$	$n_{\gamma}$
Pumpellyite	$\text{Ca}_2\text{Al}_2(\text{Al},\text{Fe},\text{Mg})[\text{Si}_2(\text{O},\text{OH})_7](\text{SiO}_4)(\text{OH},\text{O})_3$	monocl	3.21	5.5	1.688	1.695	1.705
Pyrargyrite	$\text{Ag}_3\text{SbS}_3$	rhomb	5.85	2.5	2.88	3.08	
Pyrite	$\text{FeS}_2$	cub	5.02	6.3			
Pyrochlore	$\text{NaCaNb}_2\text{O}_6\text{F}$	cub	5.3	5.3			
Pyrochroite	$\text{Mn}(\text{OH})_2$	hex	3.26	2.5	1.68	1.72	
Pyrolusite	$\text{MnO}_2$	tetr	5.08	6.3			
Pyromorphite	$\text{Pb}_5(\text{PO}_4)_3\text{AsO}_4\text{Cl}$	hex	7.04	3.8	2.048	2.058	
Pyrope	$\text{Mg}_3\text{Al}_2\text{Si}_3\text{O}_{12}$	cub	3.58	6.8	1.714		
Pyrophyllite	$\text{Al}_2\text{Si}_4\text{O}_{10}(\text{OH})_2$	monocl	2.78	1.5	1.545	1.579	1.599
Pyrrhotite	$\text{Fe}_7\text{S}_8$	hex	4.62	4			
Quartz	$\text{SiO}_2$	hex	2.65	7	1.544	1.553	
Rammelsbergite	$\text{NiAs}_2$	orth	7.1	5.8			
Raspite	$\text{PbWO}_4$	monocl	8.46	2.8	1.27	1.27	1.30
Realgar	$\text{As}_4\text{S}_4$	monocl	3.5	1.8	2.538	2.684	2.704
Rhodochrosite	$\text{MnCO}_3$	hex	3.70	3.8	1.597	1.816	
Rhodonite	$(\text{Mn},\text{Fe},\text{Ca})\text{SiO}_3$	orth	3.48	6	1.725	1.729	1.737
Riebeckite	$\text{Na}_2\text{Fe}_5(\text{Si}_8\text{O}_{22})(\text{OH})_2$	monocl	3.3	5	1.675	1.683	1.694
Rutile	$\text{TiO}_2$	tetr	4.23	6.2	2.609	2.900	
Safflorite	$(\text{Co},\text{Fe})\text{As}_2$	rhomb	7.3	4.8			
Samarskite	$(\text{Y},\text{Er},\text{Ce},\text{U},\text{Ca},\text{Fe},\text{Pb},\text{Th})(\text{Nb},\text{Ta},\text{Ti},\text{Sn})_2\text{O}_6$	rhomb	5.69	5.5	2.200		
Sapphirine	$(\text{Mg},\text{Fe})_3\text{Al}_4\text{O}_6\text{SiO}_4$	monocl	3.49	7.5	1.709	1.712	1.715
Scapolite	$(\text{Na},\text{Ca})_3\text{Al}_3(\text{Al},\text{Si})_3\text{Si}_6\text{O}_{24}(\text{Cl},\text{F},\text{OH},\text{CO}_3,\text{SO}_4)$	tetr	2.64	5.5	1.551	1.573	
Scheelite	$\text{CaW}\text{O}_4$	tetr	6.06	4.8	1.920	1.936	
Scolecite	$\text{CaAl}_2\text{Si}_3\text{O}_{10} \cdot 3\text{H}_2\text{O}$	monocl	2.27	5	1.510	1.518	1.519
Scorodite	$\text{Fe}(\text{AsO}_4)_2 \cdot 2\text{H}_2\text{O}$	rhomb	3.28	3.8	1.784	1.795	1.814
Sellaite	$\text{MgF}_2$	tetr	3.15	5	1.378	1.390	
Senarmontite	$\text{Sb}_2\text{O}_3$	cub	5.58	2.3	2.087		
Serpentine	$\text{Mg}_3\text{Si}_2\text{O}_5(\text{OH})_4$	monocl	2.55	3	1.55	1.56	1.56
Siderite	$\text{FeCO}_3$	hex	3.9	4.3	1.635	1.875	
Sillimanite	$\text{Al}_2\text{OSiO}_4$	rhomb	3.25	7	1.658	1.660	1.660
Skutterudite	$(\text{Co},\text{Ni})\text{As}_3$	cub	6.8	5.8			
Smithsonite	$\text{ZnCO}_3$	rhomb	4.4	4.3	1.621	1.848	
Sodalite	$\text{Na}_8\text{Al}_6\text{Si}_6\text{O}_{24}\text{Cl}_2$	cub	2.30	5.8	1.485		
Sperrylite	$\text{PtAs}_2$	cub	10.58	6.5			
Spessartite	$\text{Mn}_3\text{Al}_2\text{Si}_3\text{O}_{12}$	cub	4.19	6.8	1.800		
Sphalerite	$\text{ZnS}$	cub	4.0	3.8	2.369		
Sphene	$\text{CaTiSiO}_4(\text{O},\text{OH},\text{F})$	monocl	3.50	5	1.90	1.95	2.03
Spinel	$\text{MgAl}_2\text{O}_4$	cub	3.55	7.8	1.719		
Spodumene	$\text{LiAlSi}_2\text{O}_6$	monocl	3.13	6.8	1.656	1.662	1.671
Stannite	$\text{Cu}_2\text{Fe}_5\text{Sn}_4$	tetr	4.4	4			
Staurolite	$(\text{Fe},\text{Mg},\text{Zn})_2(\text{Al},\text{Fe},\text{Ti})_9\text{O}_6[(\text{Si},\text{Al})\text{O}]_4(\text{O},\text{OH})_2$	monocl	3.79	7.5	1.743	1.747	1.755
Stercorite	$\text{Na}(\text{NH}_4)\text{H}(\text{PO}_4) \cdot 4\text{H}_2\text{O}$	tric	1.62	2	1.439	1.442	1.469
Stibiotantalite	$\text{Sb}(\text{Ta},\text{Nb})\text{O}_4$	rhomb	6.6	5.5	2.38	2.41	2.46
Stibnite	$\text{Sb}_2\text{S}_3$	orth	4.56	2			
Stilbite	$\text{NaCa}_2[\text{Al}_5\text{Si}_{13}\text{O}_{36}] \cdot 14\text{H}_2\text{O}$	monocl	2.2	3.8	1.492	1.499	1.503
Stilpnomelane	$(\text{K},\text{Na},\text{Ca})_0.6(\text{Fe},\text{Mg})_6\text{Si}_8\text{Al}(\text{O},\text{OH})_{27} \cdot 2\text{H}_2\text{O}$	monocl	2.8	3.5	1.585	1.665	1.665
Stolzite	$\text{PbWO}_4$	tetr	8.2	2.8	2.19	2.27	
Strengite	$\text{FePO}_4 \cdot 2\text{H}_2\text{O}$	orth	2.87	4	1.707	1.719	1.741
Strontianite	$\text{SrCO}_3$	orth	3.5	3.5	1.518	1.666	1.668
Struvite	$\text{Mg}(\text{NH}_4)(\text{PO}_4) \cdot 6\text{H}_2\text{O}$	rhomb	1.71	2	1.495	1.496	1.504
Sulfur	$\text{S}$	orth	2.07	2	1.958	2.038	2.245
Sylvanite	$(\text{Ag},\text{Au})\text{Te}_2$	monocl	8.16	1.8			
Sylvite	$\text{KCl}$	cub	1.99	2	1.490		
Talc	$\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2$	monocl	2.71	1	1.545	1.592	1.595
Tantalite	$(\text{Fe},\text{Mn})(\text{Ta},\text{Nb})_2\text{O}_6$	rhomb	7.95	6.5	2.26	2.32	2.43
Tapiolite	$\text{FeTa}_2\text{O}_6$	tetr	7.9	6.3	2.27	2.42	
Tellurobismuthite	$\text{Bi}_2\text{Te}_3$	hex	7.74	1.8			
Terlinguaite	$\text{Hg}_2\text{OCl}$	monocl	8.73	2.5	2.35	2.64	2.66
Tetrahedrite	$(\text{Cu},\text{Fe})_{12}\text{Sb}_4\text{S}_{13}$	cub	4.9	3.8			
Thenardite	$\text{Na}_2\text{SO}_4$	orth	2.7	2.8	1.468	1.475	1.483

Name	Formula	Crystal system	Density g/cm <sup>3</sup>	Hardness	Index of refraction		
					<i>n</i> <sub>α</sub>	<i>n</i> <sub>β</sub>	<i>n</i> <sub>γ</sub>
Thermonatrite	Na <sub>2</sub> CO <sub>3</sub> ·H <sub>2</sub> O	orth	2.25	1.3	1.420	1.506	1.524
Thomsenolite	NaCaAlF <sub>6</sub> ·H <sub>2</sub> O	monocl	2.98	2	1.407	1.414	1.415
Thorianite	ThO <sub>2</sub>	cub	10.0	6.5	2.200		
Thorite	ThSiO <sub>4</sub>	tetr	6.7	4.8	1.8		
Topaz	Al <sub>2</sub> SiO <sub>4</sub> (OH,F) <sub>2</sub>	rhomb	3.53	8	1.618	1.620	1.627
Torbernite	Cu(UO <sub>2</sub> ) <sub>2</sub> (PO <sub>4</sub> ) <sub>2</sub> ·8H <sub>2</sub> O	tetr	3.22	2.3	1.582	1.592	
Tourmaline	Na(Mg,Fe,Mn,Li,Al) <sub>3</sub> Al <sub>6</sub> Si <sub>6</sub> O <sub>18</sub> (BO <sub>3</sub> ) <sub>3</sub>	rhomb	3.14	7	1.62	1.65	
Tremolite	Ca <sub>2</sub> Mg <sub>5</sub> Si <sub>8</sub> O <sub>22</sub> (OH,F) <sub>2</sub>	monocl	3.0	5.5	1.599	1.612	1.622
Trevorite	NiFe <sub>2</sub> O <sub>4</sub>	cub	5.33	7.8	2.3		
Tridymite	SiO <sub>2</sub>	hex	2.27	7	1.475	1.476	1.479
Triphyllite-Lithiophyllite	Li(Fe,Mn)PO <sub>4</sub>	rhomb	3.46	4.5	1.68	1.68	1.69
Troegerite	(UO <sub>2</sub> ) <sub>3</sub> (AsO <sub>4</sub> ) <sub>2</sub> ·12H <sub>2</sub> O	tetr		2.5	1.59	1.630	
Troilite	FeS	hex	4.7	4			
Trona	Na <sub>3</sub> H(CO <sub>3</sub> ) <sub>2</sub> ·2H <sub>2</sub> O	monocl	2.14	2.8	1.412	1.492	1.540
Turquois	Cu(Al,Fe) <sub>6</sub> (PO <sub>4</sub> ) <sub>4</sub> (OH) <sub>8</sub> ·4H <sub>2</sub> O	tricl	2.9	5.3	1.70	1.73	1.75
Ullmannite	NiSbS	cub	6.65	5.3			
Uraninite	UO <sub>2</sub>	cub	11.0	5.5			
Uvarovite	Ca <sub>3</sub> Cr <sub>2</sub> Si <sub>3</sub> O <sub>12</sub>	cub	3.83	6.8	1.865		
Valentinite	Sb <sub>2</sub> O <sub>3</sub>	orth	5.7	2.8	2.18	2.35	2.35
Vanadinite	Pb <sub>5</sub> (VO <sub>4</sub> ) <sub>3</sub> Cl	hex	6.8	2.9	2.350	2.416	
Variseite-Strengite	(Al,Fe)(PO <sub>4</sub> )·2H <sub>2</sub> O	rhomb	2.72	4	1.635	1.654	1.668
Vaterite	CaCO <sub>3</sub>	hex	2.71		1.550	1.645	
Vermiculite	(Mg,Ca) <sub>0.7</sub> (Mg,Fe,Al) <sub>6</sub> [(Al,Si) <sub>8</sub> O <sub>20</sub> ]·(OH) <sub>4</sub> ·8H <sub>2</sub> O	monocl	2.3	1.5	1.542	1.556	1.556
Vesuvianite	Ca <sub>10</sub> (Mg,Fe) <sub>2</sub> Al <sub>4</sub> (Si <sub>2</sub> O <sub>7</sub> ) <sub>2</sub> (SiO <sub>4</sub> ) <sub>5</sub> (OH,F) <sub>4</sub>	tetr	3.33	6.5	1.72	1.73	
Villaumite	NaF	cub	2.78	2.3	1.327		
Vivianite	Fe <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub> ·8H <sub>2</sub> O	monocl	2.58	1.8	1.598	1.629	1.652
Wagnerite	Mg <sub>2</sub> (PO <sub>4</sub> )F	monocl	3.15	5.3	1.568	1.572	1.582
Wavellite	Al <sub>3</sub> (OH) <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub> ·5H <sub>2</sub> O	rhomb	2.36	3.6	1.527	1.535	1.553
Whewellite	CaC <sub>2</sub> O <sub>4</sub> ·H <sub>2</sub> O	cub	2.2	2.8	1.491	1.554	1.650
Willemite	Zn <sub>2</sub> SiO <sub>4</sub>	hex	4.1	5.5	1.691	1.719	
Witherite	BaCO <sub>3</sub>	orth	4.29	3.5	1.529	1.676	1.677
Wolframite	(Fe,Mn)WO <sub>4</sub>	monocl	7.3	4.3	2.26	2.32	2.42
Wollastonite	CaSiO <sub>3</sub>	monocl	2.92	4.8	1.628	1.639	1.642
Wulfenite	PbMoO <sub>4</sub>	tetr	6.7	2.9	2.283	2.403	
Wurtzite	ZnS	hex	4.09	3.8	2.356	2.378	
Xenotime	YPO <sub>4</sub>	tetr	4.8	4.5	1.721	1.816	
Zeunerite	Cu(UO <sub>2</sub> ) <sub>2</sub> (AsO <sub>4</sub> ) <sub>2</sub> ·10H <sub>2</sub> O	tetr			1.606		
Zincite	ZnO	hex	5.6	4	2.013	2.029	
Zircon	ZrSiO <sub>4</sub>	tetr	4.6	7.5	1.94	1.99	
Zoisite	Ca <sub>2</sub> Al <sub>3</sub> Si <sub>3</sub> O <sub>12</sub> (OH)	rhomb	3.26	6	1.695	1.699	1.711