

PERMITTIVITY (DIELECTRIC CONSTANT) OF INORGANIC SOLIDS

H. P. R. Frederikse

This table lists the permittivity ϵ , frequently called the dielectric constant, of a number of inorganic solids. When the material is not isotropic, the individual components of the permittivity are given. A superscript S indicates a measurement made under constant strain ("clamped" dielectric constant). If the constraint is removed, the measurement yields ϵ^T , the "unclamped" or free dielectric constant.

The temperature of the measurement is given when available; the symbol r.t. indicates a value at nominal room temperature. The

frequency of the measurement is given in the last column (i.r. indicates a measurement in the infrared).

Substances are listed in alphabetical order by chemical formula.

Reference

Young, K. F. and Frederikse, H. P. R., *J. Phys. Chem. Ref. Data*, 2, 313, 1973.

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
Ag ₃ AsS ₃	Silver thioarsenate (Proustite)	$\epsilon_{11}^T = 16.5, \epsilon_{11}^S = 14.5$	r.t.	2×10^7
		$\epsilon_{33}^T = 20.0, \epsilon_{11}^S = 18.0$	r.t.	2×10^7
AgBr	Silver bromide	12.50	r.t.	
AgCN	Silver cyanide	5.6	r.t.	10^6
AgCl	Silver chloride	11.15	r.t.	
AgNO ₃	Silver nitrate	9.0	293	5×10^5
AgNa(NO ₂) ₂	Silver sodium nitrite	4.5 ± 0.5	r.t.	9.4×10^9
Ag ₂ O	Silver oxide	8.8	r.t.	
(AlF) ₂ SiO ₄	Aluminum fluosilicate (topaz)	$\epsilon_{11} = 6.62$	297	7×10^3
		$\epsilon_{22} = 6.58$	297	7×10^3
		$\epsilon_{33} = 6.95$	297	7×10^3
		$\epsilon_{11} = \epsilon_{22} = 9.34$	298	$10^2 - 8 \times 10^9$
Al ₂ O ₃	Aluminum oxide (alumina)	$\epsilon_{33} = 11.54$	298	$10^2 - 8 \times 10^9$
		$\epsilon_{11}^T = 6.05$	r.t.	10^3
AlPO ₄	Aluminum phosphate		r.t.	10^3
AlSb	Aluminum antimonide	11.21	300	i.r.
AsF ₃	Arsenic trifluoride	5.7	r.t.	
BN	Boron nitride	7.1	r.t.	i.r.
BaCO ₃	Barium carbonate	8.53	291	2×10^5
Ba(COOH) ₂	Barium formate	$\epsilon_{11} = 7.9$	r.t.	10^3
		$\epsilon_{22} = 5.9$	r.t.	10^3
		$\epsilon_{33} = 7.5$	r.t.	10^3
BaCl ₂	Barium chloride	9.81	r.t.	
BaCl ₂ · 2H ₂ O	Barium chloride dihydrate	9.00	r.t.	10^3
BaF ₂	Barium fluoride	7.32	292	$5 \times 10^2 - 10^{11}$
Ba(NO ₃) ₂	Barium nitrate	4.95	292	2×10^5
Ba ₂ NaNb ₅ O ₁₅	Barium sodium niobate ("Bananas")	$\epsilon_{11}^S = 222, \epsilon_{11}^T = 235$	296	10^4
		$\epsilon_{22}^S = 227, \epsilon_{22}^T = 247$	296	
		$\epsilon_{33}^S = 32, \epsilon_{33}^T = 51$	296	
BaO	Barium oxide (baria)	34 ± 1	248, 333	60×10^7
BaO ₂	Barium peroxide	10.7	r.t.	2×10^6
BaS	Barium sulfide	19.23	r.t.	7.25×10^6
BaSO ₄	Barium sulfate	11.4	288	10^8
BaSnO ₃	Barium stannate	18	298	25×10^5
BaTiO ₃	Barium titanate	$\epsilon_{11}^T = 3600$	298	10^5
		$\epsilon_{11}^S = 2300$	298	2.5×10^8
		$\epsilon_{33}^T = 150$	298	10^5
		$\epsilon_{33}^S = 80$	298	2.5×10^8
Ba ₆ Ti ₂ Nb ₈ O ₃₀	Barium titanium niobate	$\epsilon_{11} = \epsilon_{22} \approx 190$	298	
		$\epsilon_{33} \approx 220$	298	
BaWO ₄	Barium tungstate	$\epsilon_{11} = \epsilon_{22} = 35.5 \pm 0.2$	297.5	1.6×10^3
		$\epsilon_{33} = 37.2 \pm 0.2$	297.5	1.6×10^3

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
BaZrO ₃	Barium zirconate	43	rt.	
Be ₃ Al ₂ Si ₆ O ₁₈	Beryllium aluminum silicate (Beryl)	$\epsilon_{33} = 5.95$	297	7×10^3
		$\epsilon_{11} = \epsilon_{22} = 6.86$	297	7×10^3
BeCO ₃	Beryllium carbonate	9.7	291	2×10^5
BeO	Beryllium oxide (beryllia)	7.35 ± 0.2	293	2×10^6
BiFeO ₃	Bismuth iron oxide	40 ± 3	300	9.4×10^9
		$\epsilon_{11}^S = 38$	rt.	
Bi ₁₂ GeO ₂₀	Bismuth germanite		rt.	
Bi(GeO ₄) ₃	Bismuth germanate	16	293	
Bi ₂ O ₃	Bismuth sesquioxide	18.2	rt.	2×10^6
Bi ₄ Ti ₃ O ₁₂	Bismuth titanate	112	rt.	10^3
C	Diamond			
	Type I	5.87 ± 0.19	300	10^3
	Type IIa	5.66 ± 0.04	300	10^3
C ₄ H ₄ O ₆	Tartaric acid	$\epsilon_{11} = \epsilon_{22} = 4.3$	298	
		$\epsilon_{33} = 4.5$	298	
		$\epsilon_{13} = 0.55$	298	
C ₆ H ₁₄ N ₂ O ₆	Ethylene diamine tartrate (EDT)	$\epsilon_{11}^T = 5.0$	293	
		$\epsilon_{22}^T = 8.3$	293	
		$\epsilon_{33}^T = 6.0$	293	
		$\epsilon_{13}^T = 0.7$	293	
C ₆ H ₁₂ O ₆ NaBr	Dextrose sodium bromide	$\epsilon_{11}^T = 4.0$	rt.	10^3
(CH ₃ NH ₃)Al(SO ₄) ₂ · 2H ₂ O	Methyl ammonium alum (MASD)	19	197	
Ca ₂ B ₆ O ₁₁ · 5H ₂ O	Colemanite	$\epsilon_{11} = 20$	293	10^3
		$\epsilon_{33} = 25$	293	10^3
CaCO ₃	Calcium carbonate	$\epsilon_{11} = 8.67$	rt.	9.4×10^{10}
		$\epsilon_{22} = 8.69$	rt.	9.4×10^{10}
		$\epsilon_{33} = 8.31$	rt.	9.4×10^{10}
CaCeO ₃	Calcium cerate	21	rt.	
CaF ₂	Calcium fluoride	6.81	300	$5 \times 10^2 - 10^{11}$
CaMoO ₄	Calcium molybdate	$\epsilon_{11} = \epsilon_{22} = 24.0 \pm 0.2$	297.5	<10
		$\epsilon_{33} = 20.0 \pm 0.2$	297.5	<10
Ca(NO ₃) ₂	Calcium nitrate	6.54	292	2×10^5
CaNb ₂ O ₆	Calcium niobate	$\epsilon_{11} = 22.8 \pm 1.9$	rt.	$(5-500) \times 10^3$
Ca ₂ Nb ₂ O ₇	Calcium pyroniobate	~45	rt.	5×10^7
CaO	Calcium oxide	11.8 ± 0.3	283	2×10^6
CaS	Calcium sulfide	6.699	rt.	7.25×10^6
CaSO ₄ · 2H ₂ O	Calcium sulfate dihydrate	$\epsilon_{11} = 5.10$	rt.	
		$\epsilon_{22} = 5.24$	rt.	
		$\epsilon_{33} = 10.30$	rt.	
CaTiO ₃	Calcium titanate	165	rt.	
CaWO ₄	Calcium tungstate	$\epsilon_{11} = \epsilon_{22} = 11.7 \pm 0.1$	297.5	1.59×10^3
		$\epsilon_{33} = 9.5 \pm 0.2$	297.5	1.59×10^3
Cd ₃ As ₂	Cadmium arsenide	$\epsilon_{33} = 18.5$	4	
CdBr ₂	Cadmium bromide	8.6	293	5×10^5
CdF ₂	Cadmium fluoride	8.33 ± 0.08	300	$10^5 - 10^7$
CdS	Cadmium sulfide	$\epsilon_{11} = \epsilon_{22} = 8.7$	300	i.r.
		$\epsilon_{33} = 9.25$	300	i.r.
		$\epsilon_{11} = \epsilon_{22} = 8.37$	8	i.r.
		$\epsilon_{33} = 9.00$	8	i.r.
		$\epsilon_{11}^T = 8.48$	77	10^4
		$\epsilon_{33}^T = 9.48$	77	10^4
		$\epsilon_{11}^S = 9.02, \epsilon_{11}^T = 9.35$	298	10^4
		$\epsilon_{33}^S = 9.53, \epsilon_{33}^T = 10.33$	298	10^4
CdSe	Cadmium selenide	$\epsilon_{11}^S = 9.53, \epsilon_{11}^T = 9.70$	298	10^4

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
		$\epsilon_{33}^S = 10.2, \epsilon_{33}^T = 10.65$	298	10^4
CdTe	Cadmium telluride	$\epsilon_{11} = \epsilon_{22} = 10.60 \pm 0.15$	297	i.r.
		$\epsilon_{33} = 7.05 \pm 0.05$	297	i.r.
$\text{Cd}_2\text{Nb}_2\text{O}_7$	Cadmium pyroniobate	500–580	293	10^3
CeO_2	Cerium oxide	7.0	r.t.	2×10^6
CoNb_2O_6	Cobalt niobate	$\epsilon_{11} = 18.4 \pm 1.1$	r.t.	$(5-500) \times 10^3$
		$\epsilon_{22} = 21.4 \pm 1.1$	r.t.	$(5-500) \times 10^3$
		$\epsilon_{33} = 33.0 \pm 0.7$	r.t.	$(5-500) \times 10^3$
CoO	Cobalt oxide	12.9	298	$10^2 - 10^{10}$
Cr_2O_3	Chromic sesquioxide	$\epsilon_{11} = \epsilon_{22} = 13.3$	298.5	10^3
		$\epsilon_{33} = 11.9$	298.5	10^3
		8	315 (T_N)	6×10^{10}
$\text{CsAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$	Cesium alum	5.0	r.t.	$20-20 \times 10^3$
CsBr	Cesium bromide	6.38	298	1.6×10^3
Cs_2CO_3	Cesium carbonate	6.53	291	2×10^5
CsCl	Cesium chloride	7.2	298	
CsH_2AsO_4	Cesium dihydrogen arsenate (CDA)	4.8	273	9.5×10^9
CsH_2PO_4	Cesium dihydrogen phosphate (CDP)	6.15	285	9.5×10^9
$\text{CsH}_3(\text{SeO}_3)_2$	Cesium trihydrogen selenite	$\epsilon_{11} = 80$	273	10^5
		$\epsilon_{22} = 63$	273	10^5
		$\epsilon_{33} = 12$	273	10^5
CsI	Cesium iodide	6.31	298	1.6×10^3
CsNO_3	Cesium nitrate	$\epsilon_{11} = \epsilon_{22} = 9.4$	r.t.	5×10^5
		$\epsilon_{33} = 8.3$	r.t.	5×10^5
CsPbCl_3	Cesium lead chloride	14.37	300	$10^5 - 10^6$
CuBr	Cuprous bromide	8.0	293	5×10^5
CuCl	Cuprous chloride	9.8 ± 0.5	r.t.	10^3
CuO	Cupric oxide	18.1	r.t.	2×10^6
Cu_2O	Cuprous oxide (Cuprite)	7.60 ± 0.06	r.t.	10^5
$\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$	Cupric sulfate pentahydrate	6.60	r.t.	
EuF_2	Europium fluoride	7.7 ± 0.2	298	$(1-300) \times 10^3$
$\text{Eu}_2(\text{MoO}_4)_3$	Europium molybdate	9.5	298	
EuS	Europium sulfide	13.10 ± 0.04	80	$5 \times 10^2 - 10^5$
FeO	Ferrous oxide	14.2	r.t.	2×10^6
Fe_2O_3	Ferric sesquioxide	4.5	r.t.	$10^5 - 10^7$
$\text{Fe}_2\text{O}_3 - \alpha$	Ferric sesquioxide (hematite)	12		6×10^{10}
Fe_3O_4	Ferrosferric oxide (magnetite)	20	r.t.	$10^5 - 10^7$
GaAs	Gallium arsenide	13.13	300	
		12.90	4	i.r.
GaP	Gallium phosphide	11.1	r.t.	
		10.75 ± 0.1	1.6	i.r.
GaSb	Gallium antimonide	15.69	r.t.	
		15.7	4	i.r.
$\text{Gd}_2(\text{MoO}_4)_3$	Gadolinium molybdate	$\epsilon^T = 10$	298	
		$\epsilon^S = 9.5$	298	10^3
Ge	Germanium	16.0 ± 0.3	4	9.2×10^9
		15.8 ± 0.2	r.t.	$500-3 \times 10^{10}$
GeO_2	Germanium dioxide	$\epsilon_{11} = \epsilon_{22} = 7.44$	r.t.	i.r.
HIO_3	Iodic acid	$\epsilon_{11} = 7.5$	r.t.	10^3
		$\epsilon_{22} = 12.4$	r.t.	10^3
		$\epsilon_{33} = 8.1$	r.t.	10^3
$\text{HNH}_4(\text{ClCH}_2\text{COO})_2$	Hydrogen ammonium dichloroacetate	$\epsilon_{[102]} = 5.9$	r.t.	10^5
H_2O	Ice I (P = 0 kbar)	99	243	
	Ice III (P = 3 kbar)	117	243	
	Ice V (P = 5 kbar)	114	243	
	Ice VI (P = 8 kbar)	193	243	
HgCl	Mercurous chloride (Calumel)	$\epsilon_{11} = \epsilon_{22} = 14.0$	r.t.	10^{12}
HgCl_2	Mercuric chloride	6.5	r.t.	10^{12}
HgS	Mercurous sulfide (Cinnabar)	$\epsilon_{11} = \epsilon_{22} = 18.0$	r.t.	i.r.
		$\epsilon_{33} = 32.5$	r.t.	i.r.

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
HgSe	Mercurous selenide	25.6	rt.	10^4-10^6
I ₂	Iodine	$\epsilon_{11} = 6$	rt.	$5 \times 10^4-10^7$
		$\epsilon_{22} = 3$	rt.	$5 \times 10^4-10^7$
		$\epsilon_{33} = 40$	rt.	$5 \times 10^4-10^7$
InAs	Indium arsenide	14.55 ± 0.3	rt.	i.r.
		15.15	4	i.r.
InP	Indium phosphide	12.61	rt.	i.r.
InSb	Indium antimonide	17.88	4	i.r.
KAl(SO ₄) ₂ · 12H ₂ O	Potassium alum	6.5	rt.	$20-20 \times 10^3$
KBr	Potassium bromide	4.88	300	
		4.53	4.2	
KBrO ₃	Potassium bromate	7.3	rt.	2×10^6
KCN	Potassium cyanide	6.15	rt.	2×10^6
K ₂ CO ₃	Potassium carbonate	4.96	291	2×10^5
K ₂ C ₄ H ₄ O ₆ · 1/2 H ₂ O	Dipotassium tartrate (DKT)	$\epsilon_{11} = 6.44$	rt.	
		$\epsilon_{22} = 5.80$	rt.	
		$\epsilon_{33} = 6.49$	rt.	
		$\epsilon_{13} = 0.005$	rt.	
KCl	Potassium chloride	4.86 ± 0.02	rt.	5×10^3
		4.50	4.2	
KClO ₃	Potassium chlorate	5.1	rt.	2×10^6
KClO ₄	Potassium perchlorate	5.9	rt.	2×10^6
K ₂ CrO ₄	Potassium chromate	7.3	rt.	6×10^7
KCr(SO ₄) ₂ · 12H ₂ O	Potassium chrome alum	6.5	100-240	175×10^3
KD ₂ AsO ₄	Potassium dideuterium arsenate (KDDA)	$\epsilon_{11} = 70$	298	
		$\epsilon_{33} = 31$	298	
KD ₂ PO ₄	Potassium dideuterium phosphate (KDDP)	50 ± 2	297	10^3
KF	Potassium fluoride	6.05		2×10^6
KH ₂ AsO ₄	Potassium dihydrogen arsenate (KDA)	$\epsilon_{11} = 60$	298	
		$\epsilon_{33} = 24$	298	
KH ₂ PO ₄	Potassium dihydrogen phosphate (KDP)	46	298	10^3
		$\epsilon_{11} = 42$	rt.	
		$\epsilon_{33} = 21$	rt.	
K ₂ HPO ₄	Dipotassium monohydrogen orthophosphate	9.05	rt.	2×10^6
KI	Potassium iodide	5.00	rt.	9.4×10^{10}
KIO ₃	Potassium iodate	170	255	10^5
		10	293	10^5
		$\epsilon_{[101]} \approx 40,70$	rt.	10^5
		16.85	rt.	2×10^6
(K,H)Al ₃ (SiO ₃) ₃	Mica (muscovite)	5.4	299	$10^2-3 \times 10^9$
(K,H)Mg ₃ Al(SiO ₃) ₃	Mica (Canadian)	$\epsilon_{11} = \epsilon_{22} = 6.9$	298	10^2-10^4
		$\epsilon_{33} = 7.3$	298	10^4
KNO ₂	Potassium nitrite	25	305	
KNO ₃	Potassium nitrate	4.37	293	2×10^5
KNbO ₃	Potassium niobate	700	rt.	
K ₃ PO ₄	Potassium orthophosphate	7.75	rt.	2×10^6
KSCN	Potassium thiocyanate	7.9	rt.	2×10^6
K ₂ SO ₄	Potassium sulfate	6.4	rt.	2×10^6
K ₂ S ₃ O ₆	Potassium trithionate	5.7	293	1.8×10^6
K ₂ S ₄ O ₆	Potassium tetrathionate	5.5	293	1.8×10^6
K ₂ S ₅ O ₆ · H ₂ O	Potassium pentathionate	7.8	293	1.8×10^6
K ₂ S ₆ O ₆	Potassium hexathionate	7.8	293	1.8×10^6
		$\epsilon_{11} = 5.9$	rt.	10^3
K ₂ SeO ₄	Potassium selenate	$\epsilon_{22} = 7.7$	rt.	10^3
		$\epsilon_{11} = \epsilon_{11} \approx 1200$	298	
KSr ₂ Nb ₃ O ₁₅	Potassium strontium niobate	$\epsilon_{33} \approx 800$	298	
		34,000	273	10^4
KTaNbO ₃	Potassium tantalate niobate (KTN)	6,000	293	10^4
		242	298	2×10^5
KTaO ₃	Potassium tantalate	30	rt.	
LaScO ₃	Lanthanum scandate			

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
LiBr	Lithium bromide	12.1	rt.	2×10^6
Li ₂ CO ₃	Lithium carbonate	4.9	291	2×10^5
LiCl	Lithium chloride	11.05	rt.	2×10^6
LiD	Lithium deuteride	14.0 ± 0.5	rt.	i.r.
LiF	Lithium fluoride	9.00	298	10^2 – 10^7
		9.11	353	10^2 – 10^7
LiGaO ₂	Lithium metagallate	$\epsilon_{11}^T = 7.0, \epsilon_{22}^T = 6.0$	rt.	
		$\epsilon_{33}^T = 9.5$	rt.	
		$\epsilon_{11}^S = 6.8, \epsilon_{22}^S = 5.8$	rt.	
Li ⁶ H	Lithium-6 hydride	13.2 ± 0.5	rt.	
Li ⁷ H	Lithium-7 hydride	12.9 ± 0.5	rt.	
LiH ₃ (SeO ₃) ₂	Lithium trihydrogen selenite	29	298	10^4
		$\epsilon_{11} = 13.0$	rt.	
		$\epsilon_{22} = 12.9$	rt.	
		$\epsilon_{33} = 46$	rt.	
LiI	Lithium iodide	11.03	rt.	2×10^6
LiIO ₃	Lithium iodate	$\epsilon_{11} = \epsilon_{22} = 65$	294.5	10^3
		$\epsilon_{33} = 554$	298	
LiNH ₄ C ₄ O ₆ · H ₂ O	Lithium ammonium tartrate (LAT)	$\epsilon_{11}^T = 7.2$	298	
		$\epsilon_{22}^T = 8.0$	298	
		$\epsilon_{33}^T = 6.9$	298	
LiNa ₃ CrO ₄ · 6H ₂ O	Lithium trisodium chromate	8.0	rt.	10^3
LiNa ₃ MoO ₄ · 6H ₂ O	Lithium trisodium molybdate	$\epsilon_{11} = 6.7$	rt.	10^3
		$\epsilon_{33} = 5.3$	rt.	10^3
LiNbO ₃	Lithium niobate	$\epsilon_{11} = \epsilon_{22} = 82$	298	10^5
		$\epsilon_{33} = 30$	298	10^5
Li ₂ SO ₄ · H ₂ O	Lithium sulfate monohydrate	$\epsilon_{11} = 5.6$	298	
		$\epsilon_{22} = 10.3$	298	
		$\epsilon_{33} = 6.5$	298	
		$\epsilon_{13} = 0.07$	298	
LiTaO ₃	Lithium tantalate	$\epsilon_{11} = \epsilon_{22} = 53$	rt.	10^5
		$\epsilon_{33} = 46$	rt.	10^5
		$\epsilon_{11}^S = \epsilon_{22}^S = 41$	rt.	
		$\epsilon_{33}^S = 43$	rt.	
		$\epsilon_{11}^T = \epsilon_{22}^T = 51$	rt.	
		$\epsilon_{33}^T = 45$	rt.	
LiTlC ₄ O ₆ · H ₂ O	Lithium thallium tartrate (LTT)	$\epsilon_{11} \approx 20$	80	
Mg ₃ B ₇ O ₁₃ Cl	Magnesium borate monochloride (boracite)	$\epsilon_{11} = 14.1$	rt.	5×10^5
MgCO ₃	Magnesium carbonate	8.1	291	2×10^5
MgNb ₂ O ₆	Magnesium niobate	$\epsilon_{11} = 16.4 \pm 0.5$	rt.	$(5-500) \times 10^3$
		$\epsilon_{22} = 20.9 \pm 0.5$	rt.	$(5-500) \times 10^3$
		$\epsilon_{33} = 32.4 \pm 0.5$	rt.	$(5-500) \times 10^3$
MgO	Magnesium oxide (Periclase)	9.65	298	10^2 – 10^8
(MgO) _x Al ₂ O ₃	Spinel	8.6	rt.	
MgSO ₄	Magnesium sulfate	8.2	rt.	
MgSO ₄ · 7H ₂ O	Magnesium sulfate heptahydrate	5.46	rt.	
MgTiO ₃	Magnesium titanate	13.5	rt.	
MgWO ₄	Magnesium tungstate	$\epsilon_{11} = 18.0 \pm 1$	rt.	$(5-500) \times 10^3$
		$\epsilon_{22} = 18.0 \pm 1$	rt.	$(5-500) \times 10^3$
MnNb ₂ O ₆	Manganese niobate	$\epsilon_{11} = 17.4 \pm 2$	rt.	$(5-500) \times 10^3$
		$\epsilon_{22} = 16.1 \pm 0.5$	rt.	$(5-500) \times 10^3$
		$\epsilon_{33} = 30.7 \pm 1$	rt.	$(5-500) \times 10^3$
MnO	Manganese oxide (Pyrolusite)	12.8	rt.	6×10^{10}
MnO ₂	Manganese dioxide	$\sim 10^4$	298	10^4
Mn ₂ O ₃	Manganese sesquioxide	8	rt.	6×10^{10}
MnWO ₄	Manganese tungstate	$\epsilon_{11} = 19.3 \pm 1.3$	rt.	$(5-500) \times 10^3$

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
$\text{N}(\text{CH}_3)_4\text{HgBr}_3$	Tetramethylammonium tribromomercurate (TTM)	$\epsilon_{22} = 14.3 \pm 0.5$	rt.	$(5-500) \times 10^3$
		$\epsilon_{33} = 16.5 \pm 1.1$	rt.	$(5-500) \times 10^3$
		~ 10	233-373	
$\text{N}(\text{CH}_3)_4\text{HgI}_3$	Tetramethylammonium triiodo mercurate (TTM)	~ 10	233-373	
$\text{N}_4(\text{CH}_2)_6$	Hexamethylene tetramine (HMTA)	2.6 ± 0.2	rt.	10^9-10^{10}
$(\text{ND}_4)_2\text{BeF}_4$	Deuteroammonium fluoberyllate	$\epsilon_{11} = 10$	rt.	
		$\epsilon_{22} = 9$	rt.	
		$\epsilon_{33} = 9$	rt.	
		$\epsilon_{11} = 9$	rt.	
$(\text{ND}_4)_2\text{SO}_4$	Deuteroammonium sulfate	$\epsilon_{22} = 10$	rt.	
		$\epsilon_{33} = 9$	rt.	
		$\epsilon_{11} = 9$	rt.	
$(\text{NH}_2 \cdot \text{CH}_2\text{COOH})_3 \cdot \text{H}_2\text{SO}_4$	Triglycine sulfate (TGS)	$\epsilon_{11} = 9$	273	10^4
		$\epsilon_{22} = 30$	273	10^4
		$\epsilon_{33} = 6.5$	273	10^4
$(\text{NH}_2 \cdot \text{CH}_2\text{COOH})_3 \cdot \text{H}_2\text{SeO}_4$	Triglycine selenate (TGSe)	200	293	1.6×10^3
$(\text{NH}_2 \cdot \text{CH}_2\text{COOH})_3 \cdot \text{H}_2\text{BeF}_4$	Triglycine fluorberyllate (TGFB)	$\epsilon_{22} = 12$	273	10^4
$\text{NH}_4\text{Al}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$	Ammonium alum	6	rt.	10^{12}
$(\text{NH}_4)_2\text{BeF}_4$	Ammonium fluorberyllate	$\epsilon_{11} = \epsilon_{22} = 7.8$	123	10^5
		$\epsilon_{33} = 7.1$	123	10^5
		$\epsilon_{11} = \epsilon_{22} = 8.8$	293	10^5
		$\epsilon_{33} = 9.2$	293	10^5
NH_4Br	Ammonium bromide	7.1	rt.	7×10^5
NH_4I	Ammonium iodide	9.8	rt.	
$(\text{NH}_4)_2\text{C}_2\text{H}_6\text{O}_6$	Ammonium tartrate	$\epsilon_{11} = 6.45$	rt.	10^3
		$\epsilon_{22} = 6.8$	rt.	10^3
		$\epsilon_{33} = 6.0$	rt.	10^3
$(\text{NH}_4)_2\text{Cd}_2(\text{SO}_4)_3$	Ammonium cadmium sulfate	10.0	rt.	10^4
NH_4Cl	Ammonium chloride	6.9	rt.	7×10^5
$\text{NH}_4(\text{ClCH}_2\text{COO})$	Ammonium monochloroacetate	5	rt.	2×10^6
$\text{NH}_4\text{Cr}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$	Ammonium chrome alum	6.5	rt.	175×10^3
NH_4HSO_4	Ammonium bisulfate	165	273	5×10^4
$\text{NH}_4\text{H}_2\text{AsO}_4$	Ammonium dihydrogen arsenate (ADA)	5.1	265	9.5×10^9
		$\epsilon_{11} = \epsilon_{22} = 85$	298	10^3
		$\epsilon_{33} = 22$	298	
$\text{NH}_4\text{H}_2\text{PO}_4$	Ammonium dihydrogen phosphate (ADP)	$\epsilon_{11} = \epsilon_{22} = 57.1 \pm 0.6$	294.5	$10^5-35 \times 10^9$
		$\epsilon_{33} = 14.0 \pm 0.3$	294	$10^5-36 \times 10^9$
		$\epsilon_{11} = \epsilon_{22} = 74, \epsilon_{33} = 24$	300	
$\text{NH}_4\text{D}_2\text{PO}_4$	Ammonium dideuterium phosphate (ADDP)			
NH_4NO_3	Ammonium nitrate	10.7	322	$(5-50) \times 10^3$
$(\text{NH}_4)_2\text{SO}_4$	Ammonium sulfate	$\epsilon_{11} = \epsilon_{22} = 8.0$	123	10^5
		$\epsilon_{33} = 6.3$	123	10^5
		$\epsilon_{11} = \epsilon_{22} = 10.0$	293	10^5
		$\epsilon_{33} = 9.3$	293	10^5
$(\text{NH}_4)_2\text{UO}_2(\text{C}_2\text{O}_4)_2$	Ammonium uranyl oxalate	8.03	rt.	$10^4-3.3 \times 10^9$
$(\text{NH}_4)_2\text{UO}_2(\text{C}_2\text{O}_4)_2 \cdot 3\text{H}_2\text{O}$	Ammonium uranyl oxalate trihydrate	6.06	rt.	$10^4-3.3 \times 10^9$
NaBr	Sodium bromide	6.44	298	1.6×10^3
NaBrO_3	Sodium bromate	$\epsilon_{11}^T = 5.70$	298	10^3
NaCN	Sodium cyanide	7.55	293	10^5
NaCO_3	Sodium carbonate	8.75	291	2×10^5
$\text{NaCO}_3 \cdot 10\text{H}_2\text{O}$	Sodium carbonate decahydrate	5.3	rt.	6×10^7
NaCl	Sodium chloride	5.9	298	10^2-10^7
		5.45	4.2	
NaClO_3	Sodium chlorate	$\epsilon_{11}^T = 5.76$	301	10^3
		5.28	rt.	10^3

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
NaClO ₄	Sodium perchlorate	5.76	r.t.	10 ³
NaF	Sodium fluoride	5.08 ± 0.02	r.t.	5 × 10 ³
NaH ₃ (SeO ₃) ₂	Sodium trihydrogen selenite	$\epsilon_{11} \approx 75$	273	2 × 10 ⁵
NaD ₃ (SeO ₃) ₂	Sodium trideuterium selenite	$\epsilon_{11} \approx 220$	273	2 × 10 ⁵
NaI	Sodium iodide	7.28 ± 0.03	r.t.	
NaK(C ₄ H ₂ D ₂ O ₆) · 4D ₂ O	Sodium potassium tartrate tetradeuterate (double deuterated Rochelle salt)	$\epsilon_{11} = 70$ $\epsilon_{22} = 8.9$	273 273	10 ³ 10 ³
NaK(C ₄ H ₄ O ₆) · 4H ₂ O	Sodium potassium tartrate tetrahydrate (Rochelle salt)	$\epsilon_{11} = 170$ $\epsilon_{22} = 9.1$	273 273	10 ³ 10 ³
NaNH ₄ (C ₄ H ₄ O ₆) · 4H ₂ O	Sodium ammonium tartrate (Ammonium Rochelle salt)	$\epsilon_{11} = 8.4$ $\epsilon_{22} = 9.2$ $\epsilon_{33} = 9.5$	298 298 298	
NaNbO ₃	Sodium niobate	$\epsilon_{33} = 670 \pm 13$ $\epsilon_{11} = \epsilon_{22} = 76 \pm 2$	r.t. r.t.	
NaNO ₂	Sodium nitrite	$\epsilon_{11} = 7.4$ $\epsilon_{22} = 5.5$ $\epsilon_{33} = 5.0$	r.t. r.t. r.t.	5 × 10 ⁵ 5 × 10 ⁵ 5 × 10 ⁵
NaNO ₃	Sodium nitrate	6.85	292	2 × 10 ⁵
NaSO ₄	Sodium sulfate	7.90	r.t.	
NaSO ₄ · 10H ₂ O	Sodium sulfate decahydrate	5.0	r.t.	
Na ₂ SO ₄ · 5H ₂ O	Sodium sulfate pentahydrate	7	250–290	300–10 ⁴
Na ₂ UO ₂ (C ₂ O ₄) ₂	Sodium uranyl oxalate	5.18	r.t.	
NdAlO ₃	Neodymium aluminate	17.5	r.t.	
NdScO ₃	Neodymium scandate	27	r.t.	
Ni ₃ B ₇ O ₁₃ I	Nickel iodine boracite	$\epsilon_{11} = 14$	260	
NiNb ₂ O ₆	Nickel niobate	$\epsilon_{11} = 16.0 \pm 0.5$ $\epsilon_{22} = 23.8 \pm 1.8$ $\epsilon_{33} = 31.3 \pm 2.5$	r.t. r.t. r.t.	(5–500) × 10 ³ (5–500) × 10 ³ (5–500) × 10 ³
NiO	Nickel oxide	11.9	298	10 ⁵
NiSO ₄ · 6H ₂ O	Nickel sulfate hexahydrate	$\epsilon_{11} = 6.2$ $\epsilon_{33} = 6.8$	r.t. r.t.	
NiWO ₄	Nickel tungstate	$\epsilon_{11} = 17.4 \pm 2.4$ $\epsilon_{22} = 13.6 \pm 1.0$ $\epsilon_{33} = 19.7 \pm 0.6$	r.t. r.t. r.t.	(5–500) × 10 ³ (5–500) × 10 ³ (5–500) × 10 ³
P	Phosphorous (red)	4.1	r.t.	10 ⁸
	Phosphorous (yellow)	3.6	r.t.	10 ⁸
[P(CH ₃) ₄]HgBr ₃	Tetramethylphosphonium tribromomercurate (TTM)	~10	233–373	
PbBr ₂	Lead bromide	>30	293	(0.5–3) × 10 ⁶
PbCO ₃	Lead carbonate	18.6	288	10.8
Pb(C ₂ H ₃ O ₂) ₂	Lead acetate	2.6	290–295	10 ⁶
PbCl ₂	Lead chloride	33.5	273	(0.5–3) × 10 ⁶
Pb ₂ CoWO ₆	Lead cobalt tungstate	~250	r.t.	
PbF ₂	Lead fluoride	26.3	r.t.	
PbHfO ₃	Lead hafnate	390	300	10 ⁵
		185	400	
PbI ₂	Lead iodide	20.8	293	(0.5–3) × 10 ⁶
Pb ₃ MgNb ₂ O ₉	Lead magnesium niobate	10,000	297	
PbMoO ₄	Lead molybdate	$\epsilon_{11} = 34.0 \pm 0.4$ $\epsilon_{33} = 40.6 \pm 0.2$	297.5 297.5	1.6 ± 10 ³ 1.6 ± 10 ³
Pb(NO ₃) ₂	Lead nitrate	16.8	r.t.	(0.5–3) × 10 ⁶
PbNb ₂ O ₆	Lead niobate	$\epsilon_{33}^T = 180$	298	
PbO	Lead oxide	25.9	r.t.	2 × 10 ⁶
PbS	Lead sulfide (Galena)	190	77	i.r.
		200 ± 35	r.t.	i.r.
PbSO ₄	Lead sulfate	14.3	290–295	10 ⁶
PbSe	Lead selenide	280	r.t.	i.r.
PbTa ₂ O ₆	Lead metatantalate	$\epsilon_{11} = \epsilon_{22} \approx 300$ $\epsilon_{33} = 150$	r.t. r.t.	10 ⁴ 10 ⁴
PbTe	Lead telluride	450	r.t.	i.r.

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
		40	77	$10^4-15 \times 10^4$
		430	4.2	$10^4-15 \times 10^4$
PbTiO ₃	Lead titanate	~200	rt.	10^3
PbWO ₄	Lead tungstate	$\epsilon_{11} = \epsilon_{22} = 23.6 \pm 0.3$	297.5	1.59×10^3
		$\epsilon_{33} = 31.0 \pm 0.4$	297.5	1.59×10^3
Pb(Zn _{1/3} Nb _{2/3})O ₃	Lead zinc niobate	7	300	$10^3, 300 \times 10^3$
PbZrO ₃	Lead zirconate	200	400	
RbAl(SO ₄) ₂ · 12H ₂ O	Rubidium alum	5.1	rt.	10^{12}
RbBr	Rubidium bromide	4.83	300	
Rb ₂ CO ₃	Rubidium carbonate	4.87 ± 0.02	rt.	5×10^3
RbCl	Rubidium chloride	4.91 ± 0.02	rt.	5×10^3
RbCr(SO ₄) ₂ · 12H ₂ O	Rubidium chrome alum	5.0	rt.	10^{12}
RbF	Rubidium fluoride	5.91	rt.	2×10^6
RbHSO ₄	Rubidium bisulfate	$\epsilon_{11} = 7$	rt.	10^5
		$\epsilon_{22} = 8$	rt.	10^5
		$\epsilon_{33} = 10$	rt.	10^5
RbH ₂ AsO ₄	Rubidium dihydrogen arsenate (RDA)	3.90	273	9.5×10^9
RbH ₂ PO ₄	Rubidium dihydrogen phosphate (RDP)	6.15	285	9.5×10^9
RbI	Rubidium iodide	4.94 ± 0.02	rt.	5×10^3
RbInSO ₄	Rubidium indium sulfate	6.85	rt.	
RbNO ₃	Rubidium nitrate	20—380	433—488	10^6
		30	488—538	10^6
S	Sulfur	$\epsilon_{11} = 3.75$	298	10^2-10^3
		$\epsilon_{22} = 3.95$	298	10^2-10^3
		$\epsilon_{33} = 4.44$	298	10^2-10^3
	sublimed	3.69	298	10^2-10^3
SC(NH ₂) ₂	Thiourea	$\epsilon_{11} = \epsilon_{22} \approx 3$	77—300	10^3
		$\epsilon_{22} = 35$	300	10^3
Sb ₂ O ₃	Antimonous sesquioxide	12.8	rt.	$(1.5-2) \times 10^3$
Sb ₂ S ₃	Antimonous sulfide (stibnite)	$\epsilon_{11} = \epsilon_{33} = 15$	rt.	10^3
		$\epsilon_{33} = 180$	rt.	10^3
Sb ₂ Se ₃	Antimonous selenide	~110	rt.	$(10-16.5) \times 10^9$
SbSI	Antimonous sulfide iodide	2000	273	10^5
		$\epsilon_{11} = \epsilon_{22} \approx 25$	rt.	10^3-10^5
		$\epsilon_{33} \approx 5 \times 10^4$	295	10^3-10^5
Se	Selenium (monocrystal)	$\epsilon_{11} = \epsilon_{22} = 11$	300	24×10^9
		$\epsilon_{33} = 21$	300	24×10^9
	(amorphous)	6.0	298	10^2-10^{10}
Si	Silicon	12.1	4.2	10^7-10^9
SiC	Silicon carbide			
	cubic	9.72	rt.	i.r.
	6H	$\epsilon_{11} = \epsilon_{22} = 9.66$	rt.	i.r.
		$\epsilon_{33} = 10.03$	rt.	i.r.
		9.7 ± 0.1	1.8	i.r.
Si ₃ N ₄	Silicon nitride	4.2 (film)	rt.	10^3
SiO	Silicon monoxide	5.8	rt.	10^3
SiO ₂	Silicon dioxide	$\epsilon_{11} = 4.42$	rt.	9.4×10^{10}
		$\epsilon_{22} = 4.41$	rt.	9.4×10^{10}
		$\epsilon_{33} = 4.60$	rt.	9.4×10^{10}
Sm ₂ (MoO ₄) ₃	Samarium molybdate	12	298	
SnO ₂	Stannic dioxide	$\epsilon_{11} = \epsilon_{22} = 14 \pm 2$	rt.	10^4-10^{10}
		$\epsilon_{33} = 9.0 \pm 0.5$	rt.	10^4-10^{10}
SnSb	Tin antimonide	147	rt.	10^4-10^6
SnTe	Tin telluride	1770 ± 300	rt.	i.r.
Sr(COOH) ₂ · 2H ₂ O	Strontium formate dihydrate	6.1	rt.	10^3
SrCO ₃	Strontium carbonate	8.85	298	2×10^5
SrCl ₂	Strontium chloride	9.19	rt.	
SrCl ₂ · 6H ₂ O	Strontium chloride hexahydrate	8.52	rt.	
SrF ₂	Strontium fluoride	6.50	300	$5 \times 10^2-10^{11}$
SrMoO ₄	Strontium molybdate	$\epsilon_{11} = \epsilon_{22} = 31.7 \pm 0.2$	297.5	1.59×10^3

Formula	Name	ϵ_{ijk}	T/K	ν/Hz
		$\epsilon_{33} = 41.7 \pm 0.2$	297.5	1.59×10^3
$\text{Sr}(\text{NO}_3)_2$	Strontium nitrate	5.33	292	2×10^5
$\text{Sr}_2\text{Nb}_2\text{O}_7$	Strontium niobate	$\epsilon_{11} = 75$	r.t.	10^3
		$\epsilon_{22} = 46$	r.t.	10^3
		$\epsilon_{33} = 43$	r.t.	10^3
SrO	Strontium oxide	13.3 ± 0.3	273	2×10^6
SrS	Strontium sulfide	11.3	r.t.	7.25×10^6
SrSO_4	Strontium sulfate	11.5	r.t.	
SrTiO_3	Strontium titanate	332	298	10^3
		2080	78	10^3
SrWO_4	Strontium tungstate	$\epsilon_{11} = \epsilon_{22} = 25.7 \pm 0.2$	297.5	1.6×10^3
		$\epsilon_{33} = 34.1 \pm 0.2$	297.5	1.6×10^3
Ta_2O_5	Tantalum pentoxide (tantala)			
	α phase	$\epsilon_{11} = \epsilon_{22} = 30$	77	10^3
		$\epsilon_{33} = 65$	77	10^3
	β phase	24	292	10^3
$\text{Tb}(\text{MoO}_4)_3$	Terbium molybdate	11	298	
		$\epsilon_{11} = \epsilon_{22} = 33$	100–200	9.4×10^9
		$\epsilon_{33} = 53$	100–200	9.4×10^9
Te	Tellurium	$\epsilon_{11} = \epsilon_{22} = 33$	r.t.	
		$\epsilon_{33} = 54$	r.t.	
	polycrystalline	27.5	r.t.	i.r.
	monocrystalline	28.0	r.t.	i.r.
ThO_2	Thorium dioxide	18.9 ± 0.4	r.t.	3×10^5
TiO_2	Titanium dioxide (rutile)	$\epsilon_{11} = \epsilon_{22} = 86$	300	10^4 – 10^6
		$\epsilon_{33} = 170$	300	10^4 – 10^6
Ti_2O_3	Titanium sesquioxide	30	77	6×10^{10}
TlBr	Thallium bromide	30	293	10^3 – 10^7
TlCl	Thallos chloride	32.2 ± 0.2	293	10^3 – 10^5
TlI	Thallos iodide (orthorhombic)	20.7 ± 0.2	293	10^4
		37.3	193	10^7
TlNO ₃	Thallos nitrate	16.5	293	5×10^5
TlSO ₄	Thallos sulfate	25.5	293	5×10^5
UO ₂	Uranium dioxide	24	r.t.	3×10^5
WO ₃	Tungsten trioxide	300		
YMnO ₃	Yttrium manganate	20	r.t.	2×10^7
Y ₂ O ₃	Yttrium sesquioxide	10	r.t.	10^6
YbMnO ₃	Ytterbium manganate	20	r.t.	2×10^7
Yb ₂ O ₃	Ytterbium sesquioxide	5.0 (film)	r.t.	10^3
ZnO	Zinc monoxide	$\epsilon_{11}^S = 8.33$	r.t.	
		$\epsilon_{33}^S = 8.84$	r.t.	
		$\epsilon_{11}^T = 9.26$	r.t.	
		$\epsilon_{33}^T = 11.0$	r.t.	
		$\epsilon_{11} = 9.26$	r.t.	
		$\epsilon_{33} = 8.2$	r.t.	
		8.15	r.t.	i.r.
ZnS	Zinc sulfide	$\epsilon_{11}^S = 8.08 \pm 2\%$	77	10^4
		$\epsilon_{11}^S = 8.32 \pm 2\%$	298	10^4
		$\epsilon_{11}^T = 8.14 \pm 2\%$	77	10^4
		$\epsilon_{11}^T = 8.37 \pm 2\%$	298	10^4
ZnSe	Zinc selenide	$\epsilon_{11}^T = \epsilon_{11}^S = 9.12 \pm 2\%$	298	10^4
ZnTe	Zinc telluride	$\epsilon_{11}^T = \epsilon_{11}^S = 10.10 \pm 2\%$	r.t.	
ZnWO ₄	Zinc tungstate	$\epsilon_{22} = 16.1 \pm 0.5$	r.t.	$(5-500) \times 10^3$
ZrO ₂	Zirconium dioxide (zirconia)	12.5	r.t.	2×10^6