

OPTICAL PROPERTIES OF SELECTED INORGANIC AND ORGANIC SOLIDS

L. I. Berger

Optical properties of materials are closely related to their dielectric properties. The complex dielectric function (relative permittivity) of a material is equal to

$$\epsilon(\omega) = \epsilon'(\omega) - j\epsilon''(\omega),$$

where $\epsilon'(\omega)$ and $\epsilon''(\omega)$ are its real and imaginary parts, respectively, and ω is the angular frequency of the applied electric field. For a non-absorbing medium, the index of refraction is $n = (\epsilon\mu)^{1/2}$, where μ is the relative magnetic permeability of the medium (material); in the majority of dielectrics, $\mu \approx 1$.

For many applications, the most important optical properties of materials are the index of refraction, the extinction coefficient, k , and the reflectivity, R . The common index of refraction of a material is equal to the ratio of the phase velocity of propagation of an electromagnetic wave of a given frequency in vacuum to that in the material. Hence, $n \geq 1$. The optical properties of highly conductive materials like metals and semiconductors (at photon energy range above the energy gap) differ from those of optically transparent media. Free electrons absorb the incident electromagnetic wave in a thin surface layer (a few hundred nanometers thick) and then release the absorbed energy in the form of secondary waves reflected from the surface. Thus, the light reflection becomes very strong; for example, highly conductive sodium reflects 99.8% of the incident wave (at 589 nm). Introduction of the effective index of refraction, $n_{\text{eff}} = (\epsilon')^{1/2} = n - jk$, where $\epsilon' = \epsilon - j\delta/\omega \epsilon_0$, δ is the electrical conductivity of the material in S/m, and $\epsilon_0 = 8.8542 \cdot 10^{-12}$ F/m is the permittivity of vacuum, allows one to apply the expressions of the optics of transparent media to the conductive materials. It is clear that the effective index of refraction may be smaller than 1. For example, $n = 0.05$ for pure sodium and $n = 0.18$ for pure silver (at 589.3 nm). At very high photon energies, the quantum effects, such as the internal photoeffect, start playing a greater role, and the optical properties of these materials become similar to those of insulators (low reflectance, existence of Brewster's angle, etc.).

The extinction coefficient characterizes absorption of the electromagnetic wave energy in the process of propagation of a wave through a material. The wave intensity, I , after it passes a distance x in an isotropic medium is equal to

$$I = I_0 \exp(-\alpha x),$$

where I_0 is the intensity at $x = 0$ and α is called the absorption coefficient. For many applications, the extinction coefficient, k , which is equal to

$$k = \alpha \frac{\lambda}{4\pi},$$

where λ is the wavelength of the wave in the medium, is more commonly used for characterization of the electromagnetic losses in materials.

Reflection of an electromagnetic wave from the interface between two media depends on the media indices of refraction and on the angle of incidence. It is characterized by the reflectivity, which is equal to the ratio of the intensity of the wave reflected back into the first medium to the intensity of the wave approaching the interface. For polarized light and two non-absorbing media,

$$R = \frac{(N_1 - N_2)^2}{(N_1 + N_2)^2},$$

where $N_1 = n_1/\cos\theta_1$ and $N_2 = n_2/\cos\theta_2$ for the wave polarized in the plane of incidence, and $N_1 = n_1\cos\theta_1$ and $N_2 = n_2\cos\theta_2$ for the wave polarized normal to the plane of incidence; θ_1 and θ_2 are the angles between the normal to the interface in the point of incidence and the directions of the beams in the first and second medium, respectively. The reflectivity at normal incidence in this case is

$$R = [(n_1 - n_2)/(n_1 + n_2)]^2$$

For any two opaque (absorbing) media, the normal incidence reflectivity is

$$R = \frac{(n_1 - n_2)^2 + k_2^2}{(n_1 + n_2)^2 + k_2^2}.$$

In the majority of experiments, the first medium is air ($n \approx 1$), and hence,

$$R = \frac{(1 - n)^2 + k^2}{(1 + n)^2 + k^2}.$$

The data on n and k in the following table are abridged from the sources listed in the references. The reflectivity at normal incidence, R , has been calculated from the last equation. For convenience, the energy E , wavenumber \bar{v} , and wavelength λ are given for the incidence radiation.

<i>E/eV</i>	<i>ν /cm⁻¹</i>	<i>λ/μm</i>	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
Crystalline Arsenic Selenide (As_2Se_3) [Ref. 1]*											
2.194	17700	0.565				0.30					
2.168	17480	0.572				0.25					
2.141	17270	0.579				0.20					
2.123	17120	0.584				0.17					
2.098	16920	0.591				0.13					
2.094	16890	0.592					0.26				
2.091	16860	0.593					0.26				
2.073	16720	0.598				0.10	0.23				
2.060	16610	0.602					0.20				
2.049	16530	0.605				0.079	0.17				
2.036	16420	0.609					0.15				
2.023	16310	0.613					0.12				
2.013	16230	0.616				0.050					
2.009	16210	0.617					0.097				
2.000	16130	0.620					0.082				
1.987	16030	0.624					0.063				
1.977	15940	0.627				0.031					
1.974	15920	0.628					0.051				
1.962	15820	0.632					0.038				
1.953	15750	0.635					0.030				
1.949	15720	0.636				0.020					
1.937	15630	0.640					0.022				
1.925	15530	0.644					0.017				
1.922	15500	0.645				0.012					
1.905	15360	0.651				8.6·10 ⁻³					
1.893	15270	0.655				6.4					
1.881	15170	0.659				5.2					
1.859	14990	0.667				3.1					
1.848	14900	0.671					1.7·10 ⁻³				
1.845	14880	0.672				2.0					
1.842	14860	0.673					1.2·10 ⁻³				
1.831	14770	0.677				1.3·10 ⁻³	9.0·10 ⁻⁴				
1.826	14730	0.679					6.4				
1.821	14680	0.681					4.7				
1.818	14660	0.682				8.6·10 ⁻⁴					
1.815	14640	0.683					3.4				
1.807	14580	0.686				5.5					
1.802	14530	0.688				4.1					
0.06199	500.0	20.0	3.2	2.9		1.7·10 ⁻³	1.8·10 ⁻³		0.27	0.24	
0.05904	476.2	21.0	3.1	2.9		2.1·10 ⁻³	2.2·10 ⁻³		0.26	0.24	
0.05636	454.5	22.0	3.1	2.9		2.5·10 ⁻³	2.6·10 ⁻³		0.26	0.24	
0.05391	434.8	23.0	3.1	2.9		3.0·10 ⁻³	3.1·10 ⁻³				
0.04592	370.4	27.0	3.0	2.8		6.3·10 ⁻³	6.4·10 ⁻³		0.25	0.22	
0.04428	357.1	28.0	3.0	2.8		7.6·10 ⁻³	7.7·10 ⁻³		0.25	0.22	
0.04275	344.8	29.0	3.0	2.8		0.0092	0.0093		0.25	0.22	
0.04133	333.3	30.0	3.0	2.7		0.011	0.011		0.25	0.21	
0.03542	285.7	35.0	2.7	2.5			0.037	0.034	0.21	0.18	
0.03100	250.0	40.0	1.9	1.7			0.38	1.0	0.19	0.18	
0.03061	247.0	40.5	2.0	2.6			0.33	0.95	0.12	0.25	
0.03024	244.0	41.0	1.7	2.4			0.41	0.46	0.088	0.18	
0.02883	232.6	43.0	1.2	1.3			2.2	0.94	0.50	0.16	
0.02850	229.9	43.5	1.6	1.2			2.8	1.4	0.56	0.29	
0.02818	227.3	44.0	2.3	1.2		3.3	2.0		0.58	0.48	
0.02755	222.2	45.0	4.2	2.0		2.5	3.3		0.50	0.60	
0.02480	200.0	50.0	6.5	4.0		3.6	0.26		0.62	0.36	
0.02254	181.8	55.0	4.5	3.5		0.17	0.10		0.40	0.31	
0.02066	166.7	60.0	4.0	3.2		0.089	0.10		0.36	0.27	
0.01907	153.8	65.0	3.8	3.1		0.097	0.16		0.34	0.26	
0.01771	142.9	70.0	3.6	3.0		0.19	0.30		0.32	0.25	

E/eV	$\bar{\nu}$ /cm⁻¹	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.01653	133.3	75.0		3.7	3.0		0.41	0.44		0.34	0.26
0.01550	125.0	80.0		3.8	3.1		0.29	0.40		0.34	0.27
0.01459	117.6	85.0		3.6	2.9		0.20	0.34		0.32	0.24
0.01378	111.1	90.0		3.2	2.6		0.43	0.49		0.28	0.21
0.01305	105.3	95.0		4.7	3.0		1.5	1.5		0.46	0.34
0.01240	100.0	100.0		4.4	2.7		0.22	0.81		0.40	0.25
0.01181	95.24	105.0		4.2	3.0		0.094	3.9		0.38	0.62
0.01127	90.91	110.0		4.1	5.3		0.059	0.70		0.37	0.47
0.01033	83.33	120.0		3.9	4.2		0.034	0.13		0.35	0.38
0.009537	76.92	130.0		3.9	4.0		0.024	0.069		0.35	0.36
0.008856	71.43	140.0		3.9	3.8		0.019	0.048		0.35	0.34
0.007749	63.50	160.0		3.8	3.7		0.014	0.032		0.34	0.33
0.006888	55.55	180.0		3.8	3.7		0.011	0.024		0.34	0.33
0.006199	50.0	200.0		3.8	3.6		0.0091	0.019		0.34	0.32

*Indices a and c relate to the radiation electric field parallel to the a and c axes of the crystal, respectively.

Vitreous Arsenic Selenide (As_2Se_3) [Ref. 1]

2.056	16580	0.603				0.12					
2.026	16340	0.612				0.11					
2.006	16180	0.618				0.099					
1.990	16050	0.623				9.0					
1.925	15530	0.644				5.6					
1.826	14730	0.679				1.4					
1.810	14600	0.685				0.012					
1.794	14470	0.691				0.0089					
1.771	14290	0.700				6.2					
1.715	13830	0.723				2.6					
1.701	13720	0.729				0.0022					
1.647	13280	0.753				0.00046					
1.629	13140	0.761	3.07			4.0			0.62		
1.596	12870	0.777	3.06			2.7			0.49		
1.579	12740	0.785	3.05			1.9			0.39		
1.562	12590	0.794	3.05			0.00013			0.26		
1.544	12450	0.803	3.04			0.000094			0.25		
1.529	12330	0.811	3.03			6.3			0.78		
1.512	12200	0.820	3.03			4.2			0.64		
1.494	12050	0.830	3.02			2.8			0.50		
1.476	11910	0.840	3.01			1.8			0.38		
1.378	11110	0.90	2.98								
1.240	10000	1.00	2.93								
1.127	9091	1.10	2.90								
1.051	8475	1.18	2.89								
1.033	8333	1.20	2.88								
0.2555	1980	5.05				1.6·10 ⁻⁷					
0.2380	1919	5.21				9.9·10 ⁻⁸					
0.2344	1890	5.29				1.1·10 ⁻⁷					
0.1345	1085	9.22				4.4					
0.1339	1080	9.26				3.7					
0.1333	1075	9.30				4.4					
0.1308	1055	9.48				4.5					
0.1215	980	10.20				8.9					
0.1203	970	10.31				9.9·10 ⁻⁷					
0.1196	965	10.36				1.0·10 ⁻⁶					
0.1178	950	10.53				1.1					
0.1116	900	11.11				1.8					
0.1004	810	12.35				4.9					
0.09919	800	12.50				7.0·10 ⁻⁶					
0.09795	790	12.66				1.0·10 ⁻⁵					
0.09671	780	12.82				1.5					
0.09299	750	13.33				3.7					
0.08555	690	14.49				6.9					

E/eV	$\bar{\nu}$ /cm⁻¹	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.08431	680	14.71				5.9					
0.08059	650	15.38				6.1					
0.07811	630	15.87				6.3					
0.07687	620	16.13				7.7					
0.07563	610	16.39				7.8					
0.07439	600	16.67				$9.3 \cdot 10^{-5}$					
0.07315	590	16.95	2.8			$1.2 \cdot 10^{-4}$			0.22		
0.07191	580	17.24	2.8			1.4			0.32		
0.07067	570	17.54	2.8			1.8			0.37		
0.06943	560	17.86	2.8			2.8			0.50		
0.06633	535	18.69	2.8			5.2			0.73		
0.06571	530	18.87	2.8			$7.2 \cdot 10^{-4}$			0.22		
0.06509	525	19.05	2.8			$1.2 \cdot 10^{-3}$			0.22		
0.06447	520	19.23	2.8			1.7			0.35		
0.06075	490	20.41	2.7			4.9			0.71		
0.06024	485.9	20.58	2.7			5.2			0.73		
0.05331	430	23.26	2.7			1.4			0.31		
0.05269	425	23.53	2.7			$1.1 \cdot 10^{-3}$			0.21		
0.05207	420	23.81	2.7			$8.5 \cdot 10^{-4}$			0.21		
0.05145	415	24.10	2.7			7.3			0.84		
0.05083	410	24.39	2.7			8.3			0.87		
0.05021	405	24.69	2.7			$9.4 \cdot 10^{-4}$			0.21		
0.04959	400	25.0	2.7			$1.2 \cdot 10^{-3}$			0.21		
0.04862	392.2	25.5	2.6			1.6			0.33		
0.04679	377.4	26.5	2.6			5.0			0.73		
0.04592	370.4	27.0	2.6			$8.0 \cdot 10^{-3}$			0.20		
0.04509	363.6	27.5	2.6			$1.2 \cdot 10^{-2}$			0.20		
0.04428	357.1	28.0	2.6			1.7			0.34		
0.03875	312.5	32.0	2.5			8.2			0.87		
0.03815	307.7	32.5	2.5			$9.3 \cdot 10^{-3}$			0.18		
0.03757	303.0	33.0	2.4			0.11			0.17		
0.02988	241.0	41.5	2.2			0.89			0.20		
0.02952	238.1	42.0	2.2			1.0			0.22		
0.02725	219.8	45.5	3.2			1.8			0.39		
0.02362	190.5	52.5	3.6			0.30			0.32		
0.01937	156.2	64.0	3.2			0.10			0.27		
0.01922	155.0	64.5	3.2			$9.6 \cdot 10^{-2}$			0.27		
0.01907	153.8	65.0	3.2			9.4			0.88		
0.01734	139.9	71.5	3.1			8.7			0.87		
0.01653	133.3	75.0	3.1			9.4			0.88		
0.01642	132.5	75.5	3.1			0.096			0.26		
0.01494	120.5	83.0	3.0			0.15			0.25		
0.01246	100.5	99.5	3.2			0.60			0.26		
0.007606	61.35	163.0	3.3			0.12			0.29		
0.006199	50.00	200.0	3.2								
0.004592	37.04	270.0	3.1			0.072			0.26		
0.002799	22.57	443.0	3.0			4.5			0.67		
0.001826	14.73	679.0	3.0			2.8			0.50		
0.001273	10.27	974.0	3.0			2.1			0.41		
0.0006491	5.236	1910.0	3.0			$1.1 \cdot 10^{-2}$			0.25		
0.0004376	3.530	2833.0	3.0			$7.5 \cdot 10^{-3}$			0.25		
0.0002903	2.341	4271.0	3.0			5.0			0.71		
0.0001716	1.384	7224.0	3.0			3.1			0.53		
0.00009047	0.7297	13704	3.0			$1.6 \cdot 10^{-3}$			0.25		
0.00005621	0.4534	22056	3.0			$9.9 \cdot 10^{-4}$			0.25		
0.00002774	0.2237	44699	3.0			5.2			0.72		
0.00001439	0.1161	86153	3.0			2.6			0.47		

Vitreous Arsenic Sulfide (As_2S_3) - [Ref. 2]

4.959	40000	0.2500	2.48	1.21	0.27
3.100	25000	0.40	3.09	0.34	0.27

<i>E/eV</i>	<i>ν̄ /cm⁻¹</i>	<i>λ/μm</i>	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
2.48	20000	0.4999	2.83			0.013			0.23		
1.879	15150	0.66	2.59			1.7·10⁻⁶			0.20		
1.240	10000	1.0	2.48			2.4·10⁻⁷			0.18		
0.6199	5000	2.0	2.43						0.17		
0.3100	2500	4.0	2.41						0.17		
0.2480	2000	5.0	2.41						0.17		
0.1736	1400	7.143	2.40			7.4·10⁻⁷			0.17		
0.1240	1000	10.00	2.38			1.3·10⁻⁴			0.17		
0.09299	750	13.33	2.35			3.0·10⁻³			0.16		
0.07439	600	16.67	2.31			4.6·10⁻⁴			0.16		
0.04959	400.0	25.0	1.79			0.2			0.085		
0.03757	303.0	33.0	3.59			1.4			0.38		
0.03100	250.0	40.0	2.98			0.15			0.25		
0.02480	200.0	50	2.66			0.11			0.21		
0.02066	166.7	60	2.64			0.57			0.22		
0.01771	142.9	70	2.99			0.17			0.25		
0.01550	125.0	80	2.89			0.14			0.24		
0.01378	111.1	90	2.84			0.12			0.23		
0.01240	100	100	2.81			0.10			0.23		
0.008183	66	152	2.76			0.072			0.22		
0.004029	32.5	308	2.74			0.044			0.22		
0.002418	19.5	513	2.74			0.031			0.22		
0.001984	16	625	2.74			0.025			0.22		
0.001048	8.45	1180	2.73			8.8·10⁻³			0.22		
0.0001033	0.833	12000	2.73			1.3·10⁻³			0.22		
4.129·10⁻¹²	3.33·10⁻⁸	3·10¹¹	2.73						0.22		

Cadmium Telluride (CdTe) - [Ref. 3]

4.9	39520	0.2530	2.48		2.04				0.39		
4.1	33070	0.3024	2.33		1.59				0.32		
3.9	31460	0.3179	2.57		1.90				0.37		
3.5	28230	0.3542	2.89		1.52				0.34		
3.1	25000	0.4000	3.43		1.02				0.34		
3.0	24200	0.4133	3.37		0.861				0.32		
2.755	22220	0.45	3.080		0.485				0.27		
2.75	22180	0.4509	3.23		0.636				0.29		
2.610	21050	0.475	3.045								
2.5	20160	0.4959	3.14		0.525				0.28		
2.25	18150	0.5510	3.05		0.411				0.26		
1.771	14290	0.70	2.861		0.210				0.23		
1.512	12200	0.82	2.880		0.040				0.23		
1.50	12100	0.8266	2.98		0.319				0.25		
1.475	11900	0.840	2.905		0.00134				0.24		
1.47	11860	0.8434			0.000671						
1.465	11820	0.8463			3.37						
1.46	11780	0.8492			1.89						
1.459	11760	0.850	2.948						0.24		
1.455	11740	0.8521			1.08·10⁻⁴						
1.45	11690	0.8551	2.9565		5.10·10⁻⁵				0.24		
1.445	11650	0.8580			2.73						
1.442	11630	0.860	2.952						0.24		
1.44	11610	0.8610	2.9479		1.37				0.32		
1.43	11530	0.8670	2.9402						0.24		
1.30	10490	0.9537	2.8720						0.23		
1.24	10000	1.0	2.840						0.23		
1.20	9679	1.033	2.8353						0.23		
1.10	8872	1.127	2.8050						0.23		
1.00	8065	1.240	2.7793						0.22		
0.90	7259	1.378	2.7537						0.22		
0.80	6452	1.550	2.7384						0.22		
0.70	5646	1.771	2.7223						0.21		

E/eV	$\bar{\nu}$ /cm⁻¹	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.60	4839	2.066	2.7086						0.21		
0.50	4033	2.480	2.6972						0.21		
0.40	3226	3.100	2.6878						0.21		
0.30	2420	4.133	2.6800						0.21		
0.20	1613	6.199	2.6722						0.21		
0.10	806.5	12.40	2.6535						0.20		
0.09	725.9	13.78	2.6482						0.20		
0.06819	550	18.18	2.623						0.20		
0.0573	462	21.6				3.8·10 ⁻⁶					
0.05	403.3	24.80	2.5801						0.19		
0.0469	378	26.5				8.0·10 ⁻⁵					
0.04592	370.3	27				9.88·10 ⁻⁵					
0.04133	333.3	30	2.55916			2.86·10 ⁻⁴			0.19		
0.04092	330	30.30	2.531			3.34			0.57		
0.03720	300	33.33	2.494			4.97			0.73		
0.03647	294.1	34.00				8.93					
0.03596	290	34.48	2.478			5.77·10 ⁻³			0.18		
0.03493	281.7	35.5				7.91					
0.03472	280	35.71	2.459			6.76			0.83		
0.03100	250	40	2.378			1.18·10 ⁻²			0.17		
0.02917	235.3	42.5				6.93					
0.02852	230	43.48	2.289			1.87			0.36		
0.02728	220	45.45	2.224			2.47·10 ⁻²			0.14		
0.02604	210	47.62	2.137			3.4·10 ⁻²			0.13		
0.02480	200	50.00	2.013			4.97·10 ⁻²			0.11		
0.02384	192.3	52.0				6.21					
0.01798	145	68.97	1.8			5.2			0.79		
0.01736	140	71.43	6.778			4.50			0.66		
0.01550	125	80.0	4.598			0.294			0.41		
0.01364	110	90.91	3.868			9.47·10 ⁻²			0.35		
0.01240	100	100	3.649			5.68·10 ⁻²			0.32		
0.009919	80	125	3.415			0.0262			0.30		
0.008679	70	142.9	3.348			0.0189			0.29		
0.007439	60	166.7	3.299			1.39			0.35		
0.006199	50	200	3.263			1.03			0.32		
0.004959	40	250	3.236			7.52·10 ⁻³			0.28		
0.003720	30	333.3	3.217						0.28		
0.023015	18.563		538.71			3.2096			0.28		
0.001550	12.50	800				6.18					

Gallium Arsenide (GaAs) - [Ref. 4]

155		0.007999		0.0181
145		0.008551		0.0203
130		0.009537		0.0224
110		0.01127		0.0278
90		0.01378		0.0323
70		0.01771		0.0376
40		0.03100		0.0426
23		0.05391	1.037	0.228
7.0		0.1771	1.063	1.838
6.0	48390	0.2066	1.264	2.472
5.00	40330	0.2480	2.273	4.084
4.00	32260	0.3100	3.601	1.920
3.00	24200	0.4133	4.509	1.948

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
2.50	20160	0.4959	4.333			0.441			0.39		
2.00	16130	0.6199	3.878			0.211			0.35		
1.80	14520	0.8888	3.785			0.151			0.34		
1.60	12900	0.7749	3.700			0.091			0.33		
1.50	12100	0.8266	3.666			0.080			0.33		
1.40	11290	0.8856	3.6140			$1.69 \cdot 10^{-3}$			0.32		
1.20	9679	1.033	3.4920						0.31		
1.00	8065	1.240	3.4232						0.30		
0.80	6452	1.550	3.3737						0.29		
0.50	4033	2.480	3.3240						0.29		
0.25	2016	4.959	3.2978						0.29		
0.15	1210	8.266	3.2831						0.28		
0.100	806.5	12.40	3.2597			$4.93 \cdot 10^{-6}$			0.28		
0.090	725.9	13.78	3.2493			$1.64 \cdot 10^{-5}$			0.28		
0.070	564.6	17.71	3.2081			$2.32 \cdot 10^{-4}$			0.28		
0.060	483.9	20.66	3.1609			$3.45 \cdot 10^{-3}$			0.27		
0.0495	399.2	25.05	3.058			$2.07 \cdot 10^{-3}$			0.26		
0.03968	320	31.25	2.495			$2.43 \cdot 10^{-2}$			0.18		
0.03496	282	35.46	0.307			$294 \cdot 10^{-2}$					
0.02976	240	41.67	4.57			$4.26 \cdot 10^{-2}$			0.41		
0.02066	166.7	60	3.77			$3.89 \cdot 10^{-3}$			0.34		
0.01550	125	80	3.681			$1.84 \cdot 10^{-3}$			0.33		
0.008266	66.67	150	3.62			$2.14 \cdot 10^{-3}$			0.32		
0.002480	20	500	3.607			$1.3 \cdot 10^{-3}$			0.32		
0.001240	10	1000	3.606						0.32		

Gallium Phosphide (GaP) - [Ref. 5]

154.0		0.00805			$1.7 \cdot 10^{-2}$						
110.0		0.0113			$2.15 \cdot 10^{-2}$						
100.0		0.0124			$215 \cdot 10^{-2}$						
80.0		0.0155			$3.0 \cdot 10^{-2}$						
50.0		0.0248			$4.7 \cdot 10^{-2}$						
27.0		0.0459			$9.3 \cdot 10^{-2}$						
25.0		0.0496			0.122						
20.0		0.0620			0.180						
15.0		0.0826	0.748		0.628						
5.5	44360	0.2254	1.543		3.556				0.68		
4.68	37750	0.2649	4.181		2.634				0.50		
3.50	28230	0.3542	5.050		0.819				0.46		
3.00	24200	0.4133	4.081		0.224				0.37		
2.78	22420	0.4460	3.904		0.103				0.35		
2.621	21140	0.473	3.73		$6.37 \cdot 10^{-3}$				0.33		
2.480	20000	0.500	3.590		$2.47 \cdot 10^{-3}$				0.32		
2.18	17580	0.5687	3.411		$2.8 \cdot 10^{-7}$				0.30		
2.000	16130	0.62	3.3254						0.29		
1.6	12900	0.7749	3.209						0.28		
1.240	10000	1.0	3.1192						0.26		
0.6888	5556	1.8	3.0439						0.26		
0.4769	3846	2.6	3.0271						0.25		
0.1907	1538	6.5	2.995		$4.29 \cdot 10^{-4}$				0.25		
0.1550	1250	8.0	2.984						0.25		
0.1240	1000	10	2.964						0.25		
0.06199	500	20	2.615		$7.16 \cdot 10^{-3}$				0.20		
0.03100	250	40	3.594		$1.81 \cdot 10^{-2}$				0.32		

E/eV	\bar{v} /cm⁻¹	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.02480	200	50	3.461			5.77·10 ⁻³			0.30		
0.01727	139.27	71.80	3.3922			4.34·10 ⁻³			0.30		
0.01168	94.21	106.1	3.3621			4.26·10 ⁻³			0.29		
0.006199	50.00	200	3.3447			1.3·10 ⁻⁴			0.29		
0.004133	33.33	300	3.3413						0.29		
0.001240	10.00	1000	3.3319						0.29		

Indium Antimonide (InSb) - [Ref. 6]

155		0.007999				4.77·10 ⁻³					
60		0.02066				7.30·10 ⁻²					
25		0.04959	1.15			.015					
24		0.05166	1.15			0.18					
15		0.08266	0.97			0.230					
10		0.1240	0.74			0.88					
5.00	40330	0.2480	1.307			2.441			0.53		
4.50	36290	0.2755	1.443			2.894			0.60		
4.00	32260	0.3100	2.632			3.694			0.61		
3.34	26940	0.3712	3.528			2.280			0.45		
2.84	22910	0.4366	3.340			2.021			0.45		
1.80	14520	0.6888	4.909			1.396			0.47		
1.50	12100	0.8266	4.418			0.643			0.41		
0.6	4839	2.066	4.03						0.36		
0.2480	2000	5.0	4.14			9.1·10 ⁻²			0.37		
0.1907	1538	6.5	4.30			6.3·10 ⁻²			0.39		
0.1653	1333	7.5	4.18			2.7·10 ⁻²			0.38		
0.06199	500	20.00	3.869			2.0·10 ⁻³			0.35		
0.03100	250	40.00	2.98			2.6·10 ⁻³			0.25		
0.02480	200	50.00	2.22			0.165			0.14		
0.02244	181	55.25	3.05			7.59			0.84		
0.02207	178	56.18	9.61			4.20			0.70		
0.02033	164	60.98	4.94			0.140			0.44		
0.01054	85	117.6	2.12			0.423			0.14		
0.005579	45	222.2	1.02			5.59			0.88		
0.001860	15	666.7	6.03			17.9			0.93		
0.001240	10	1000	10.7			24.0			0.94		

Indium Arsenide (InAs) - [Ref. 7]

25		0.04959				1.139			0.168		
20		0.06199				1.125			0.225		
15		0.08266				0.894			0.336		
10		0.1240				0.835			1.071		
6	48390	0.2066	1.434			2.112			0.45		
5.0	40330	0.2480	1.524			2.871			0.58		
4.0	32260	0.3100	3.313			1.799			0.39		
3.5	28230	0.3542	3.008			1.754			0.37		
3.0	24200	0.4133	3.197			2.034			0.41		
2.5	20160	0.4959	4.364			1.786			0.45		
2.44	19680	0.5081	4.489			1.446			0.44		
1.86	15000	0.6666	3.889			0.554			0.36		
1.8	14520	0.6888	3.851			0.530			0.35		
1.7	13710	0.7293	3.798			0.493			0.35		
1.6	12900	0.7749	3.755			0.463			0.34		
1.5	12100	0.8266	3.714			0.432			0.34		
1.2	9679	1.033	3.613						0.32		
1.0	8065	1.240	3.548						0.31		
0.6	4839	2.066				0.161					
0.35	2823	3.542	3.608			9.58·10 ⁻³			0.32		
0.32	2581	3.875	3.512			1.23·10 ⁻⁴			0.31		
0.20	1613	6.199	3.427						0.30		
0.1240	1000	10.00	3.402						0.30		
0.06199	500	20.00	3.334						0.29		
0.04959	400	25.00	3.264						0.28		

<i>E/eV</i>	<i>ν̄ /cm⁻¹</i>	<i>λ/μm</i>	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.04339	350	28.57	3.182			5.46·10⁻³			0.27		
0.03720	300	33.33	2.988						0.25		
0.03100	250	40.00	1.970			6.37·10⁻²			0.11		
0.02765	222	44.84	5.90			6.53			0.74		
0.02480	200	50.00	6.91			0.30			0.56		
0.01984	160	62.50	5.27			0.41			0.47		
0.01860	150	66.67	5.27			0.51			0.47		
0.01736	140	71.43	3.99			1.1·10⁻²			0.36		
0.01488	120	83.33	3.91			6.6·10⁻³			0.35		
0.01240	100	100.0	3.85			4.3·10⁻³			0.35		
0.009919	80	125.0	3.817						0.34		
0.007439	60	166.7	3.793						0.34		
0.004959	40	250.0	3.778						0.34		
0.002480	20	500	3.769						0.37		
0.001240	10	1000	3.766						0.34		

Indium Phosphide (InP) - [Ref. 8]

20		0.06199	0.793		0.494						
15		0.08266	0.695		0.574						
10		0.1240	0.806		1.154						
5.5	44360	0.2254	1.426		2.562				0.79		
5.0	40330	0.2480	2.131		3.495				0.61		
4.0	32260	0.3100	3.141		1.730				0.38		
3.0	24200	0.4133	4.395		1.247				0.43		
2.0	16130	0.6199	3.549		0.317				0.32		
1.5	12100	0.8266	3.456		0.203				0.31		
1.25	10085	0.9915	3.324						0.29		
1.00	8068	1.239	3.220						0.28		
0.50	4034	2.479	3.114						0.26		
0.30	2420	4.131	3.089						0.26		
0.10	806.8	12.39	3.012						0.25		
0.075	605.1	16.53	2.932						0.24		
0.060	484.1	20.66	2.780		1.46·10⁻²				0.22		
0.050	403.4	24.79	2.429		3.35·10⁻²				0.17		
0.03992	322	31.06	0.307		3.57						
0.03496	282	35.46	3.89		0.282				0.35		
0.03100	250	40.00	4.27		3.0·10⁻²				0.39		
0.02728	220	45.45	3.93		1.3·10⁻²				0.35		
0.02480	200	50.0	3.81		8.7·10⁻³				0.34		
0.02418	195	51.28	3.19						0.27		
0.02232	180	55.56	3.19						0.27		
0.01860	150	66.67	3.65						0.32		
0.01240	100	100	3.57						0.32		
0.009919	80	125.0	3.551						0.31		
0.007439	60	166.7	3.538						0.31		
0.004959	40	250.0	3.529						0.31		
0.002480	20	500	3.523						0.31		
0.001240	10	1000.0	3.522						0.31		

Lead Selenide (PbSe) - [Ref. 9]

14.5		0.08551	0.72		0.20						
10		0.1240	0.68		0.50						
5	40330	0.2480	0.54		1.2						
2.0	16130	0.6199	3.65		2.9				0.51		
1.65	13310	0.7514	4.51		1.73				0.46		
1.5	12100	0.8266	4.64		2.64				0.52		
1.0	8065	1.240	4.65		1.1				0.44		
0.75	6049	1.653			0.269						
0.62	5001	2.000	4.59		0.770				0.42		
0.48	3871	2.583	4.90						0.44		
0.40	3226	3.100	4.91						0.44		
0.32	2581	3.875	4.98		0.173				0.44		

E/eV	\bar{v} /cm⁻¹	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.20	1613	6.199	4.82			1.20·10 ⁻³			0.43		
0.1190	960	10.42	4.74			2.09·10 ⁻³			0.42		
0.09919	800	12.50	4.72			4.12·10 ⁻³			0.42		
0.07935	640	15.63	4.68			1.00·10 ⁻²			0.42		
0.05951	480	20.83	4.59			1.77·10 ⁻²			0.41		
0.04959	400	25.00	4.49			3.62·10 ⁻²			0.40		
0.03968	320	31.25	4.31			9.61·10 ⁻²			0.39		
0.02976	240	41.67	3.89			0.56			0.24		
0.01984	160	62.50	2.34			7.38			0.18		
0.009919	80	125.0	1.73			10.1			0.88		
0.007935	64	156.3	2.91			14.6			0.90		
0.004959	40	250.0	11.2			2.88·10 ⁻²			0.88		
0.002480	20	500.0	12.6			6.17·10 ⁻²					
0.001736	14	714.3	14.1			0.171					
0.001240	10	1000	17.4			0.294					

Lead Sulfide (PbS) - [Ref. 10]

150		0.008266				3.86·10 ⁻³					
125		0.009919				5.59·10 ⁻³					
100		0.01240				1.54·10 ⁻²					
80		0.01550				2.88·10 ⁻²					
60		0.02066				6.17·10 ⁻²					
25		0.04959	0.845			0.171					
18.0		0.06888	0.846			0.294					
14.0		0.08856	0.651			0.665					
10.0		0.1240	0.879			1.050					
4.95	39920	0.2505	1.52			2.10			0.43		
4.0	32260	0.3100	1.73			2.83			0.55		
3.00	24200	0.4133	3.88			3.00			0.53		
2.90	23390	0.4275	4.12			2.70			0.51		
2.75	22180	0.4509	4.25			2.33			0.48		
2.55	20570	0.4862	4.35			2.00			0.47		
2.00	16130	0.6199	4.29			1.48			0.43		
1.60	12910	0.7749	4.62			0.94			0.43		
1.24	10000	1.00	4.43			0.597			0.41		
1.03	8333	1.2	4.30			0.458			0.39		
0.650	5263	1.9	4.24			0.318			0.39		
0.496	4000	2.5	4.30			0.235			0.39		
0.400	3226	3.1	4.30			2.27·10 ⁻²			0.39		
0.3100	2500	4.0	4.16			6.38·10 ⁻⁴			0.38		
0.2480	2000	5	4.115			9.25·10 ⁻⁴			0.37		
0.1240	1000	10	4.01			6.32·10 ⁻³			0.36		
0.1033	833.3	12	3.90			1.14·10 ⁻²			0.35		
0.08059	650	15.38	3.90						0.35		
0.06819	550	18.18	3.81						0.34		
0.04959	400	25.00	3.53						0.31		
0.03720	300	33.33	2.99						0.25		
0.02480	200.0	50	0.514			1.59					
0.01378	111.1	90	1.175			8.48			0.94		
0.01240	100.0	100	1.79			10.51			0.94		
0.008856	71.43	140	17.41			17.94			0.89		
0.006199	50.0	200	16.27			2.20			0.79		
0.003100	25.00	400	12.96			0.495			0.73		
0.001653	13.33	750	12.44			0.228			0.72		
0.001240	10.00	1000	12.35			0.167			0.72		
0.0006199	5.000	2000	12.27			0.0815			0.72		

Lead Telluride (PbTe) - [Ref. 11]

150		0.008266				2.37·10 ⁻³					
125		0.009919				9.71·10 ⁻³					
100		0.01240				4.39·10 ⁻²					
75		0.01653				6.43·10 ⁻²					

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
50		0.02480				$6.87 \cdot 10^{-2}$					
30		0.04133				$7.77 \cdot 10^{-2}$					
15		0.08266	0.72			0.17					
10		0.1240	0.66			0.60					
7.5		0.1653	0.8			0.92					
5.0	40330	0.2480	0.72			1.0					
3.0	24200	0.4133	1.0			2.2					
2.5	20160	0.4959	1.35			2.86			0.61		
1.5	12100	0.8266	3.8			3.1			0.53		
1.0	8065	1.240	4.55			2.2			0.49		
0.80	6452	1.550	6.25			0.71			0.53		
0.60	4839	2.066	6.10			0.521			0.52		
0.40	3226	3.100	6.075			0.331			0.52		
0.30	2420	4.133	5.95			$3.55 \cdot 10^{-2}$			0.51		
0.20	1613	6.199	5.77						0.50		
0.15	1210	8.266	5.76						0.50		
0.1017	820	12.20	5.47			$9.16 \cdot 10^{-3}$			0.48		
0.08927	720	13.89	5.38			$1.37 \cdot 10^{-2}$			0.47		
0.06943	560	17.86	5.13			$3.06 \cdot 10^{-2}$			0.45		
0.04959	400	25.00	4.50			$9.6 \cdot 10^{-2}$			0.40		
0.03968	320	31.25	3.58			0.23			0.32		
0.02976	240	41.67	1.01			1.9					
0.009919	80	125.0	2.95			16.6			0.96		
0.007439	60	166.7	4.9			22.5			0.96		
0.006199	50	200.0	6.9			27.2			0.97		
0.004959	40	250.0	11.6			34.8			0.97		
0.003720	30	333.3	27.7			35.7			0.95		
0.002480	20	500.0	27.6			39.1			0.95		
0.001240	10	1000	45.1			57.8			0.97		

Lithium Fluoride (LiF) - [Ref. 12]

2000		6.199·10 ⁻⁴	0.9999347	4.33·10 ⁻⁶
1496		8.287·10 ⁻⁴	0.999883	1.28·10 ⁻⁵
1016		1.220·10 ⁻³	0.999757	5.18·10 ⁻⁵
725		1.710·10 ⁻³	0.999643	1.62·10 ⁻⁴
504		2.460·10 ⁻³	0.999162	4.96·10 ⁻⁵
303		4.092·10 ⁻³	0.99752	3.12·10 ⁻⁴
250		4.959·10 ⁻³	0.99632	6.17·10 ⁻⁵
200		6.199·10 ⁻³		2.12·10 ⁻³
150		8.265·10 ⁻³	0.9899	3.54·10 ⁻³
100		1.240·10 ⁻²	0.9801	1.32·10 ⁻²
75		1.653·10 ⁻²		2.63·10 ⁻²
50		2.480·10 ⁻²		7.89·10 ⁻²
25		4.959·10 ⁻²	0.558	0.521
20		6.199·10 ⁻²	1.20	0.58
15.1		8.211·10 ⁻²	1.08	0.68
13		9.537·10 ⁻²	1.04	1.64
12.0		0.1033	2.28	0.11
11.0		0.1127	1.77	8.07·10 ⁻⁷
10.00		0.12398	1.606	7.70·10 ⁻⁷
9		0.1375	1.53	
7		0.1771	1.46	
4.959	40000	0.250	1.4189	0.03
4.000	32260	0.31	1.4073	0.03
2.952	23810	0.42	1.3978	0.03
2.000	16130	0.62	1.3915	0.03
0.9919	8000	1.25	1.3851	
0.7999	6452	1.55	1.3858	
0.4959	4000	2.5	1.3731	0.02
0.4000	3226	3.1	1.3650	
0.3100	2500	4.0	1.3493	

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
0.2480	2000	5.0	1.3266			$1.8 \cdot 10^{-6}$			0.02		
0.2000	1613	6.2	1.2912								
0.1698	1370	7.3	1.2499								
0.1494	1205	8.3	1.2036								
0.1240	1000	10.0	1.1005			$2.6 \cdot 10^{-3}$					
0.1127	909.1	11.0	1.0208			$8.0 \cdot 10^{-3}$					
0.1033	833.3	12.0				$1.9 \cdot 10^{-2}$					
0.09537	769.2	13.0				$3.7 \cdot 10^{-2}$					
0.08679	700	14.29	0.508			$7.74 \cdot 10^{-2}$					
0.07439	600	16.67	0.124			0.804					
0.06199	500	20.00	0.306			1.47			0.68		
0.05579	450	22.22	0.191			1.88			0.85		
0.04959	400	25.00	0.208			2.71			0.91		
0.03720	300	33.33	8.76			3.91			0.68		
0.03100	250	40.00	4.64			0.287			0.42		
0.02480	200	50.00	3.69			0.102			0.33		
0.01240	100.0	100	3.067			0.106			0.26		
0.06199	50.0	200	3.067			$4.0 \cdot 10^{-2}$			0.26		
0.04959	40.00	250	3.067			$2.2 \cdot 10^{-2}$			0.26		
0.02480	20.00	500	3.067			$6.3 \cdot 10^{-3}$					
0.01378	11.11	900				$3.1 \cdot 10^{-3}$					
$4.798 \cdot 10^{-4}$	3.870	2584	3.023			$1.19 \cdot 10^{-3}$			0.25		
$1.464 \cdot 10^{-4}$	1.181	8469	3.023			$6.20 \cdot 10^{-4}$			0.25		
$4.053 \cdot 10^{-5}$	0.3269	30590	3.023			$2.63 \cdot 10^{-4}$			0.25		
$1.861 \cdot 10^{-7}$	$1.501 \cdot 10^{-3}$	$6.662 \cdot 10^6$	3.018			$1.6 \cdot 10^{-5}$					
$3.718 \cdot 10^{-8}$	$2.999 \cdot 10^{-4}$	$3.335 \cdot 10^7$	3.018			$1.6 \cdot 10^{-5}$					

Potassium Chloride (KCl) - [Ref. 13]

2860.3		$4.3347 \cdot 10^{-4}$				$3.93 \cdot 10^{-6}$					
2855.3		$4.3423 \cdot 10^{-4}$				$3.39 \cdot 10^{-6}$					
2849.3		$4.3514 \cdot 10^{-4}$				$4.61 \cdot 10^{-6}$					
2835.8		$4.3721 \cdot 10^{-4}$				$5.85 \cdot 10^{-6}$					
2832.3		$4.3775 \cdot 10^{-4}$				$5.85 \cdot 10^{-6}$					
2829.8		$4.3814 \cdot 10^{-4}$				$1.57 \cdot 10^{-6}$					
2828.3		$4.3837 \cdot 10^{-4}$				$4.19 \cdot 10^{-7}$					
219		$5.661 \cdot 10^{-3}$				$1.82 \cdot 10^{-3}$					
215		$5.767 \cdot 10^{-3}$				$1.84 \cdot 10^{-3}$					
212.5		$5.834 \cdot 10^{-3}$				$2.19 \cdot 10^{-3}$					
211		$5.876 \cdot 10^{-3}$				$1.82 \cdot 10^{-3}$					
185.1		$6.7 \cdot 10^{-3}$	0.99874						$1.01 \cdot 10^{-3}$		
109.7		$1.13 \cdot 10^{-2}$	0.99578						$4.22 \cdot 10^{-3}$		
43		0.02883	0.96			$3.0 \cdot 10^{-2}$					
40		0.03179	0.925			$1.8 \cdot 10^{-2}$					
29.9		0.04147	0.756			0.145					
20.1		0.06168	0.910			0.495					
15.1		0.08211	0.965			0.344					
10.0		0.1240	1.16			0.38			0.035		
9.0		0.1378	1.99			0.50			0.13		
8.0		0.1550	1.15			0.46			0.048		
7.0		0.1771	2.0			$8.46 \cdot 10^{-7}$			0.11		
6.199	50000	0.20	1.71739						0.070		
4.959	40000	0.25	1.58972								
3.999	32260	0.31	1.54005								
2.952	23810	0.42	1.50701								
2.695	21740	0.46	1.50115						0.040		
2.616	21100	0.474				$7.6 \cdot 10^{-11}$					
2.384	19230	0.52	1.49501								
2.066	16670	0.60	1.48969						0.039		
1.550	12500	0.80	1.48291						0.038		
1.033	8333	1.2	1.47813						0.037		
0.5166	4167	2.4	1.47464						0.037		

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
0.2480	2000	5.0	1.47048						0.036		
0.2000	1.613	6.2	1.46796						0.036		
0.1512	1220	8.2	1.46260						0.035		
0.09999	806.5	12.4	1.44611						0.033		
0.07560	609.8	16.4	1.42295						0.030		
0.04959	400.0	25.0	1.34059			6.57·10 ⁻⁴			0.021		
0.03999	322.6	31.0	1.2431						0.012		
0.02976	240	41.67	0.85			0.16					
0.02728	220	45.45	0.53			0.35					
0.02232	180	55.56	0.31			1.05					
0.01860	150	66.67	0.44			4.0					
0.01612	130	76.92	4.1			0.32			0.37		
0.01240	100	100.0	2.7			0.11			0.21		
0.008679	70	142.9	2.4			9.2·10 ⁻²			0.17		
0.006199	50	200.0	2.2						0.14		
0.001240	10.00	1000				9.0·10 ⁻³					
0.0006199	5.000	2000				3.7·10 ⁻³					
0.0004133	3.333	3000				2.0·10 ⁻³					

Silicon Dioxide (Glass) - [Ref. 14]

2000		6.199·10 ⁻⁴	0.99993			1.503·10 ⁻⁵					
1860		6.665·10 ⁻⁴	0.99991			1.936·10 ⁻⁵					
1609		7.705·10 ⁻⁴	0.99989			9.941·10 ⁻⁶					
1496		8.287·10 ⁻⁴	0.99987			1.308·10 ⁻⁵					
1204		1.030·10 ⁻³	0.99980			2.916·10 ⁻⁵					
1093		1.134·10 ⁻³	0.99975			4.155·10 ⁻⁵					
1016		1.220·10 ⁻³	0.99971			5.423·10 ⁻⁵					
798		1.554·10 ⁻³	0.99954			1.289·10 ⁻⁴					
597		2.077·10 ⁻³	0.99917			3.560·10 ⁻⁴					
396		3.131·10 ⁻³	0.99812			4.04·10 ⁻⁴					
303		4.092·10 ⁻³	0.99678			9.91·10 ⁻⁴					
201		6.168·10 ⁻³	0.99269			3.63·10 ⁻³					
151.2		8.2·10 ⁻³	0.9871			7.3·10 ⁻³					
99.99		1.24·10 ⁻²	0.9813			7.0·10 ⁻³					
49.59		2.50·10 ⁻²	0.9164			6.5·10 ⁻²					
40.00		3.10·10 ⁻²	0.907			9.2·10 ⁻²					
31.00		4.00·10 ⁻²	0.851			0.156					
25.00		0.04959	0.733			0.325					
20.00		0.06199	0.859			0.585					
15.00		0.08266	1.168			0.711			0.10		
13.00		0.09537	1.368			0.747			0.11		
11.00		0.1127	1.739			0.569			0.11		
10.00		0.1240	2.330			0.323			0.17		
9.00		0.1378	1.904			1.89·10 ⁻²			0.097		
7.00		0.1771	1.600						0.053		
6.00	48390	0.2066	1.543						0.046		
4.9939	40278.4	0.248272	1.50841						0.041		
4.1034	33096.1	0.302150	1.48719						0.038		
3.0640	24712.3	0.404656	1.46961						0.036		
2.5504	20570.5	0.486133	1.46313						0.035		
2.4379	19662.5	0.508582	1.46187						0.035		
2.2705	18312.5	0.546074	1.46008						0.035		
2.1489	17332.3	0.576959	1.45885						0.035		
2.1411	17269.2	0.579065	1.45877						0.035		
2.1102	17019.5	0.587561	1.45847						0.035		
2.1041	16970.4	0.589262	1.45841						0.035		
1.9257	15531.6	0.643847	1.45671						0.035		
1.8892	15237.6	0.656272	1.45637						0.035		
1.8566	14974.2	0.667815	1.45608						0.034		
1.7549	14153.9	0.706519	1.45515						0.034		
1.4550	11735.6	0.852111	1.45248						0.034		

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
1.0985	8860.06	1.12866	1.44888						0.034		
0.60243	4858.9	2.0581	1.43722						0.032		
0.35354	2851.4	3.5070	1.40568						0.028		
0.2976	2400	4.176	1.383			$1.07 \cdot 10^{-4}$			0.026		
0.2728	2200	4.545	1.365			$2.56 \cdot 10^{-4}$			0.024		
0.2480	2000	5.000	1.342			$3.98 \cdot 10^{-3}$			0.021		
0.2232	1800	5.556	1.306			$5.63 \cdot 10^{-3}$					
0.1984	1600	6.250	1.239			$6.52 \cdot 10^{-3}$					
0.1736	1400	7.143	1.053			$1.06 \cdot 10^{-2}$					
0.1674	1350	7.407	0.9488			$1.48 \cdot 10^{-2}$					
0.1612	1300	7.692	0.7719			$3.72 \cdot 10^{-2}$					
0.1500	1210	8.265	0.4530			0.704			0.30		
0.1401	1130	8.850	0.3563			1.53			0.66		
0.1302	1050	9.524	2.760			1.65			0.35		
0.1209	975	10.26	2.448			0.231			0.18		
0.1091	880	11.36	1.784			$7.75 \cdot 10^{-2}$			0.079		
0.09919	800	12.50	1.753			0.343			0.089		
0.08989	725	13.79	1.698			0.175			0.071		
0.06943	560	17.86	1.337			0.298			0.036		
0.06199	500	20.00	0.6616						0.882		
0.04959	400	25.0	2.739			0.397			0.23		
0.03720	300	33.33	2.210			$6.7 \cdot 10^{-2}$			0.14		
0.01240	100	100.0	1.967			$1.59 \cdot 10^{-2}$			0.11		
0.007439	60	166.7	1.959			$8.62 \cdot 10^{-3}$			0.11		
0.002480	20	500.0	1.955			$7.96 \cdot 10^{-3}$			0.10		

Silicon Monoxide (Noncrystalline) - [Ref. 15]

25		0.04959	0.8690			0.2717					
20		0.06199	0.8853			0.4919					
17.5		0.07085	0.9825			0.5961					
15		0.08266	1.132			0.6651			0.092		
12.5		0.09919	1.283			0.6523			0.090		
10		0.1240	1.378			0.6843			0.10		
7.5		0.1653	1.593			0.7473			0.12		
5	40330	0.2480	2.001			0.6052			0.15		
4	32260	0.3100	2.141			0.4006			0.15		
3	24200	0.4133	2.116			0.1211			0.13		
2.8	22580	0.4428	2.085			0.08374			0.12		
2.6	20970	0.4769	2.053			0.05544			0.12		
2.4	19360	0.5166	2.021			0.03533			0.11		
2.2	17740	0.5636	1.994			0.02153			0.11		
2	16130	0.6199	1.969			0.01175			0.11		
1.8	14520	0.6888	1.948			0.00523			0.10		
1.6	12900	0.7749	1.929			0.00151			0.10		
1.240	10000	1.000	1.87						0.092		
0.6199	5000	2.000	1.84						0.087		
0.3100	2500	4.000	1.80						0.082		
0.2480	2000	5.000	1.75						0.074		
0.2066	1667	6.000	1.70						0.067		
0.1771	1492	7.000	1.60						0.053		
0.1653	1333	7.500	1.42								
0.1459	1176	8.500	0.90			0.18					
0.1305	1053	9.500	1.20			1.20			0.024		
0.1240	1000	10.00	2.00			1.38			0.27		
0.1181	952.4	10.50	2.85			0.90			0.27		
0.1153	930.2	10.75	2.86			0.58			0.25		
0.1127	909.1	11.00	2.82			0.40			0.24		
0.1078	869.6	11.50	2.50			0.20			0.19		
0.1033	833.3	12.00	2.13			0.14			0.13		
0.09537	769.2	13.00	2.04			0.20			0.12		
0.08856	714.3	14.00	2.01			0.30			0.12		

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
Noncrystalline Silicon Nitride (Si_3N_4) - [Ref. 16]											
24		0.05166	0.655		0.420				0.28		
23		0.05391	0.625		0.481				0.22		
22		0.05636	0.611		0.560				0.16		
21		0.05904	0.617		0.647				0.19		
20		0.06199	0.635		0.743				0.21		
19		0.06526	0.676		0.841				0.23		
18		0.06888	0.735		0.936				0.26		
17		0.07293	0.810		1.03				0.25		
16		0.07749	0.902		1.11				0.26		
15		0.08266	1.001		1.18				0.26		
14		0.08856	1.111		1.26				0.26		
13		0.09537	1.247		1.35				0.27		
12	96790	0.1033	1.417		1.43				0.28		
11	88720	0.1127	1.657		1.52				0.29		
10.5	84690	0.1181	1.827		1.53				0.29		
10	80650	0.1240	2.000		1.49				0.29		
9.5	76620	0.1305	2.162		1.44				0.28		
9	72590	0.1378	2.326		1.32				0.27		
8	64520	0.1550	2.651		0.962				0.26		
7	56460	0.1771	2.752		0.493				0.23		
6	48390	0.2066	2.541		0.102				0.19		
5	40330	0.2480	2.278		$4.9 \cdot 10^{-3}$				0.15		
4.75	38310	0.2610	2.234		$1.2 \cdot 10^{-3}$				0.15		
4.5	36290	0.2755	2.198		$2.2 \cdot 10^{-4}$				0.14		
4	32260	0.3100	2.141						0.13		
3.5	28230	0.3542	2.099						0.13		
3	24200	0.4133	2.066						0.12		
2.5	20160	0.4959	2.041						0.12		
2	16130	0.6199	2.022						0.11		
1.5	12100	0.8266	2.008						0.11		
1	8065	1.240	1.998						0.11		
Sodium Chloride (NaCl) - [Ref. 17]											
209.5		$5.918 \cdot 10^{-3}$			$2.54 \cdot 10^{-3}$						
206		$6.019 \cdot 10^{-3}$			$2.62 \cdot 10^{-3}$						
203		$6.107 \cdot 10^{-3}$			$2.08 \cdot 10^{-3}$						
200		$6.199 \cdot 10^{-3}$			$1.92 \cdot 10^{-3}$						
26.0		0.04769	0.83		0.15				0.015		
25.0		0.04959	0.83		0.18				0.018		
22.0		0.05636	0.83		0.31				0.057		
20.0		0.06199	0.88		0.34				0.036		
18.0		0.06888	0.89		0.33				0.033		
16.1		0.07700	0.74		0.45				0.084		
14.0		0.08856	0.98		0.89				0.17		
12.0		0.1033	1.22		0.79				0.12		
10.0		0.1240	1.55		0.71				0.12		
8.00		0.1550	1.38		1.10				0.20		
6.00	48390	0.2066	1.75						0.074		
5.00	40330	0.2480	1.65						0.060		
2.952	23810	0.42	1.56324						0.048		
2.480	20000	0.50	1.55157						0.047		
2.214	17860	0.56	1.54613						0.046		
2.000	16130	0.62	1.54228						0.045		
1.771	14290	0.70	1.53865						0.045		
1.675	13510	0.74	1.53728						0.045		
1.550	12500	0.80	1.53560						0.045		
1.240	10000	1.00	1.53200						0.044		
1.033	8333	1.2	1.53000						0.044		
0.6888	5556	1.8	1.52712						0.043		
0.4959	4000	2.5	1.52531						0.043		

E/eV	\bar{v} / cm^{-1}	$\lambda/\mu\text{m}$	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
0.4000	3226	3.1	1.52395						0.043		
0.3263	2632	3.8	1.52226			(1.8±0.2) ·10 ⁻⁹			0.043		
0.2952	2381	4.2	1.52121						0.043		
0.2755	2222	4.5	1.52036						0.043		
0.2480	2000	5.0	1.51883						0.042		
0.1240	1000	10.0	1.49473						0.039		
0.1033	833.3	12.0	1.48000						0.037		
0.08856	714.3	14.0	1.46188						0.035		
0.07749	625.0	16.0	1.4399						0.033		
0.06888	555.5	18.0	1.41364						0.029		
0.06199	500.0	20.0	1.3822						0.026		
0.04959	400	25.0	1.27			3.5·10 ⁻³			0.014		
0.04215	340	29.41	1.12			1.7·10 ⁻²			0.0032		
0.03720	300	33.33	0.85			0.85			0.18		
0.03410	275	36.36	0.59			0.22			0.084		
0.03286	265	37.74	0.42			0.50			0.26		
0.03224	260	38.46	0.45			0.45			0.22		
0.02480	200	50.00	0.14			1.99			0.89		
0.02108	170	58.82	1.35			6.03			0.87		
0.01984	160	62.50	6.92			2.14			0.59		
0.01922	155	64.52	5.50			0.87			0.49		
0.01860	150	66.67	4.52			0.380			0.41		
0.01736	140	71.43	3.72			0.219			0.33		
0.01612	130	76.92	3.31			0.135			0.29		
0.01488	120	83.33	3.02			0.110			0.25		
0.01240	100	100.0	2.74			0.087			0.22		
0.009919	80	125.0	2.57			0.077			0.19		
0.07439	60	166.7	2.48			0.055			0.18		
0.04959	40	250.00	2.44			0.041			0.18		
0.002480	20	500.0	2.43			0.024			0.17		
0.001240	10	1000	2.43			0.006			0.17		
0.001033	8.333	1200				8.8·10 ⁻³					
0.0006888	5.556	1800				5.4·10 ⁻³					
0.0006199	5.000	2000	2.43						0.17		
0.0004959	4.000	2500				4.4·10 ⁻³					
0.0004797	3.869	2584	2.43			2.1·10 ⁻³			0.17		
0.0003875	3.125	3200				3.3·10 ⁻³					
0.0001464	1.181	8469	2.43			5.8·10 ⁻⁴			0.17		
0.00004053	0.3269	30590	2.43			2.5·10 ⁻⁴					

Cubic Zinc Sulfide (ZnS) - [Ref. 18]

2000	6.199·10 ⁻⁴	0.999904	1.76·10 ⁻⁵
1204	1.030·10 ⁻³	0.999777	1.00·10 ⁻⁴
1016	1.220·10 ⁻³	0.999838	3.61·10 ⁻⁵
901	1.376·10 ⁻³	0.999647	5.42·10 ⁻⁵
798	1.554·10 ⁻³	0.999520	8.28·10 ⁻⁵
707	1.754·10 ⁻³	0.999372	1.25·10 ⁻⁴
597	2.077·10 ⁻³	0.999160	2.19·10 ⁻⁴
377	9.50·10 ⁻³	0.99789	9.50·10 ⁻⁴
201	6.168·10 ⁻³	0.99553	4.82·10 ⁻³
100	1.240·10 ⁻²	0.99061	1.17·10 ⁻²
61.99	2.000·10 ⁻²	0.964	3.32·10 ⁻²
41.33	3.000·10 ⁻²	0.941	5.10·10 ⁻²
31.00	4.000·10 ⁻²	0.847	9.95·10 ⁻²
24.80	5.000·10 ⁻²	0.796	0.171
17.71	7.000·10 ⁻²	0.747	0.431
13.78	9.000·10 ⁻²	0.758	0.824
12.40	0.1000	0.862	0.876
9.919	0.125	1.02	1.36
8.266	0.150	1.41	1.47
			6.2·10 ⁻⁴
			2.2·10 ⁻²
			7.7·10 ⁻²
			0.20
			0.19
			0.31
			0.29

<i>E/eV</i>	<i>ν /cm⁻¹</i>	<i>λ/μm</i>	<i>n</i>	<i>n_a</i>	<i>n_c</i>	<i>k</i>	<i>k_a</i>	<i>k_c</i>	<i>R</i>	<i>R_a</i>	<i>R_c</i>
6.199		0.200	2.32			1.62			0.32		
6.00	48390	0.2066	2.24			1.65			0.59		
4.00	32260	0.3100	2.70			0.44			0.22		
3.00	24200	0.4133	2.54			4·10 ⁻²			0.19		
2.50	20160	0.4959	2.42			3·10 ⁻²			0.17		
2.30	18550	0.5391	2.3950						0.17		
2.00	16130	0.6199	2.3576						0.16		
1.75	14110	0.7085	2.3319						0.16		
1.55	12500	0.7999	2.3146			3.50·10 ⁻⁶			0.16		
1.40	11290	0.8856	2.3033						0.16		
1.240	10000	1.000	2.2907			3.02·10 ⁻⁶			0.15		
1.00	8065	1.240	2.2795						0.15		
0.80	6452	1.550	2.2706						0.15		
0.6199	5000	2.000	2.2631			6.2·10 ⁻⁶			0.15		
0.45	3629	2.755	2.2587						0.15		
0.30	2420	4.133	2.2529						0.15		
0.20	1613	6.199	2.2443						0.15		
0.1550	1250	8.0	2.2213			4.5·10 ⁻⁶			0.14		
0.1240	1000	10.00	2.1986			8.8·10 ⁻⁶			0.14		
0.100	806.5	12.4	2.1969						0.14		
0.09	725.9	13.78	2.1793						0.14		
0.07999	645.2	15.5	2.1518			3.82·10 ⁻³			0.14		
0.07	564.6	17.71	2.1040						0.13		
0.06075	490	20.41	2.03			8.0·10 ⁻³			0.12		
0.05	403.3	24.80	1.6866						0.065		
0.03546	286	34.97	3.29			8.3·10 ⁻²			0.28		
0.03472	280	35.71	9.54			5.2·10 ⁻²			0.66		
0.02480	200	50.00	3.48			3.1·10 ⁻²			0.31		
0.01240	100	100.0	3.06			5.8·10 ⁻³			0.26		
0.004955	40	250.0	2.903			6.2·10 ⁻³			0.24		
0.004339	35	285.7	2.899			7.0·10 ⁻³			0.24		
0.003720	30	333.3	2.896						0.24		
0.003100	25	400.0	2.894						0.24		
0.002480	20	500.0	2.892						0.24		
0.001860	15	666.7	2.890						0.24		

Polytetrafluoroethylene (Teflon) - [Ref. 19]

4.960	40000	0.250							0.970		
4.769	38462	0.260							0.972		
4.593	37037	0.270							0.975		
4.426	35714	0.280							0.978		
4.276	34483	0.290							0.980		
4.133	33333	0.300							0.983		
4.000	32258	0.310							0.986		
3.875	31250	0.320							0.988		
3.758	30303	0.330							0.990		
3.647	29412	0.340							0.991		
3.543	28571	0.350							0.992		
3.444	27778	0.360							0.992		
3.351	27027	0.370							0.993		
2.255	18182	0.550							0.993		
2.067	16667	0.600							0.992		
1.378	11111	0.900							0.992		
1.305	10526	0.950							0.991		
1.078	8696	1.150							0.991		
1.033	8333	1.200							0.990		
0.9920	8000	1.250							0.990		
0.9538	7692	1.300							0.989		
0.9185	7407	1.350							0.988		
0.8857	7143	1.400							0.988		
0.8552	6897	1.450							0.989		

E/eV	$\bar{\nu}/\text{cm}^{-1}$	$\lambda/\mu\text{m}$	n	n_a	n_c	k	k_a	k_c	R	R_a	R_c
0.8267	6667	1.500							0.989		
0.8000	6452	1.550							0.988		
0.7750	6250	1.600							0.988		
0.7515	6061	1.650							0.987		
0.7294	5882	1.700							0.986		
0.7086	5714	1.750							0.986		
0.6889	5556	1.800							0.985		
0.6703	5405	1.850							0.980		
0.6526	5263	1.900							0.978		
0.6359	51282	1.950							0.978		
0.6200	5000	2.000							0.970		
0.6049	4878	2.050							0.959		
0.5905	4762	2.100							0.951		
0.5767	4651	2.150							0.946		
0.5636	4545	2.200							0.966		
0.5511	44444	2.250							0.965		
0.5487	44247	2.260							0.964		
0.5439	4386	2.280							0.963		
0.5415	4367	2.290							0.961		
0.5368	4329	2.310							0.959		
0.5345	4310	2.320							0.957		
0.5322	4292	2.330							0.956		
0.5299	4274	2.340							0.954		
0.5277	4255	2.350							0.951		
0.5232	4219	2.370							0.950		
0.5188	4184	2.390							0.949		
0.5167	4167	2.400							0.947		
0.5061	4082	2.450							0.946		
0.4960	4000	2.500							0.945		

References

1. Arsenic Selenide

D. J. Treacy in *Handbook of Optical Constants of Solids*, E. D. Palik, Editor, Academic Press, 1985, p. 623. (Hereafter abbreviated as HOCS.)

R. Zallen, R. E. Drews, R. L. Emerald, and M. L. Slade, *Phys. Rev. Lett.* 26, 1564 (1971).
R. Zallen, M. L. Slade, and A. T. Ward, *Phys. Rev. B* 3, 4257 (1971).
U. Strom and P. C. Taylor, *Phys. Rev. B* 16, 5512 (1977).
G. Lucovsky, *Phys. Rev. B* 6, 1480 (1972).
C. T. Moynihan, P. B. Macedo, M. S. Maklad, R. K. Mohr, and R. E. Howard, *J. Non-Cryst. Solids*, 17, 369 (1975).
Y. Ohmachi, *J. Opt. Soc. Am.* 63, 630 (1973).

2. Arsenic Sulfide

D. J. Treacy in HOCS, 1985, p. 641.
P. A. Young, *J. Phys. C* 4, 93 (1971).
W. S. Rodny, I. H. Malitson, and T. A. King, *J. Opt. Soc. Am.* 48, 633 (1958).
R. Zallen, R. E. Drew, R. L. Emerald, and M. L. Slade, *Phys. Rev. Lett.* 26, 1564 (1971).
M. S. Maklad, R. K. Mohr, R. E. Howard, P. B. Macedo, and C. T. Moynihan, *Solid State Commun.* 15, 855 (1974).
P. B. Klein, P. C. Taylor, and D. J. Treacy, *Phys. Rev. B* 16, 4511 (1977).
G. Lucovsky, *Phys. Rev. B* 6, 1480 (1972).

3. Cadmium Telluride

E. D. Palik in HOCS, 1985, p. 409.
D. T. F. Marple and H. Ehrenreich, *Phys. Lett.* 8, 87 (1962).
T. H. Myers, S. W. Edwards, and J. F. Schetzina, *J. Appl. Phys.* 52, 4231 (1981).
D. T. F. Marple, *Phys. Rev.* 150, 728 (1966).
A. N. Pikhtin and A. D. Yas'kov, *Sov. Phys. Semicond.* 12, 622 (1978).
L. S. Ladd, *Infrared Phys.* 6, 145 (1966).
J. E. Harvey and W. L. Wolfe, *J. Opt. Soc. Am.* 65, 1267 (1975).

A. Manabe, A. Mitsuishi, and H. Yoshinaga, *Jpn. J. Appl. Phys.* 6, 593 (1967).

A. Manabe, A. Mitsuishi, H. Oshinaga, Y. Ueda, and H. Sei, *Technol. Rep. Osaka Univ. Jpn.* 17, 263 (1967).

J. R. Birch and D. K. Murray, *Infrared Phys.* 18, 283 (1978).

4. Gallium Arsenide

E. D. Palik in HOCS, 1985, p. 429.
M. Cardona, W. Gudat, B. Sonntag, and P. Y. Yu, in *Proc. Intl. Conf. Phys. Semicond.*, 10th. Cambridge, 1970, p. 208. US Atom. Energy Commission, Oak Ridge, TN, 1970.
H. R. Philipp and H. Ehrenreich, *Phys. Rev.* 129, 1550 (1963).
J. B. Theeten, D. E. Aspnes, and R. P. H. Chang, *J. Appl. Phys.* 49, 6097 (1978).
H. C. Casey, D. D. Sell, and K. W. Wecht, *J. Appl. Phys.* 46, 250 (1975).
A. H. Kachare, W. G. Spitzer, F. K. Euler, and A. Kahan, *J. Appl. Phys.* 45, 2938 (1974).
R. T. Holm, J. W. Gibson, and E. D. Palik, *J. Appl. Phys.* 48, 212 (1977).
W. Cochran, S. J. Fray, F. A. Johnson, J. E. Quarrington, and N. Williams, *J. Appl. Phys. Suppl.* 32, 2102 (1961).
C. P. Christensen, R. Joiner, S. K. T. Nieh, and W. H. Steier, *J. Appl. Phys.* 45, 4957 (1974).
R. H. Stolen, *Phys. Rev. B* 11, 767 (1975); *Appl. Phys. Lett.* 15, 74 (1969).

5. Gallium Phosphide

A. Borghesi and G. Guizzetti in HOCS, 1985, p. 445.
M. Cardona, W. Gudat, B. Sonntag, and P. Y. Yu, *Proc. Intl. Conf. Phys. Semicond.* Cambridge, 1970, p. 208. US Atom. Energy Commission, Oak Ridge, TN, 1970.
M. Cardona, W. Gudat, E. E. Koch, M. Skibowski, B. Sonntag, and P. Y. Yu, *Phys. Rev. Lett.* 25, 659 (1970).
S. E. Stokowski and D. D. Sell, *Phys. Rev. B* 5, 1636 (1972).
S. A. Abagyan, G. A. Ivanov, Y. E. Shanurin, and V. I. Amosov, *Sov. Phys. Semicond.* 5, 889 (1971).
P. G. Dean, G. Kaminsky, and R. B. Zetterstrom, *J. Appl. Phys.* 38, 3551 (1967).

- D. E. Aspnes and A. A. Studna, *Phys. Rev. B* 27, 985 (1983).
6. Indium Antimonide
R. T. Holm in *HOCS*, 1985, p. 491.
M. Cardona, W. Gudat, B. Sonntag, and P. Y. Yu, *Proc. Int. Conf. Phys. Semicond.*, 10th. Cambridge, 1970, p. 208. US Atom. Comm., Oak Ridge, TN, 1970.
H. R. Philipp and H. Ehrenreich, *Phys. Rev.* 129, 1550 (1963).
D. E. Aspnes and A. A. Studna, *Phys. Rev. B* 27, 985 (1983).
T. S. Moss, S. D. Smith, and T. D. F. Hawkins, *Proc. Phys. Soc. London* 70B, 776 (1957).
H. Yoshinaga and R. A. Oetjen, *Phys. Rev.* 101, 526 (1956).
R. B. Sanderson, *J. Phys. Chem. Solids* 26, 803 (1965).
7. Indium Arsenide
E. D. Palick and R. T. Holm in *HOCS*, 1985, p. 479.
H. R. Philipp and H. Ehrenreich, *Phys. Rev.* 129, 1550 (1963).
B. O. Seraphin and H. E. Bennett in *Semiconductors and Semimetals* (R. K. Willardson and A. C. Beer, Eds.), vol. 3, Academic, 1967, p. 499.
D. E. Aspnes and A. A. Studna, *Phys. Rev. B* 27, 985 (1983).
J. R. Dixon and J. M. Ellis, *Phys. Rev.* 123, 1560 (1961).
A. Memon, T. J. Parker, and J. R. Birch, *Proc. SPIE*, 289, 20 (1981).
8. Indium Phosphide
O. J. Glembocki and H. Piller in *HOCS*, 1985, p. 503.
M. Cardona, *J. Appl. Phys.* 32, 958 (1961); 36, 2181 (1965).
D. E. Aspnes and A. A. Studna, *Phys. Rev. B* 27, 985 (1983).
G. D. Pettit and W. J. Turner, *J. Appl. Phys.* 36, 2081 (1965).
R. Newman, *Phys. Rev.* 111, 1518 (1958).
W. N. Reynolds, M. T. Lilburne, and R. M. Dell, *Proc. Phys. Soc. London* 71, 416 (1958).
H. Jamshidi and T. J. Parker, Int. Meet. Infrared Mm. Waves, 7th., Marseilles, 1983.
9. Lead Selenide
G. Bauer and H. Krenn in *HOCS*, 1985, p. 517.
M. Cardona and D. L. Greenaway, *Phys. Rev. A* 133, 1685 (1964).
T. S. Moss, *Optical Properties of Semiconductors*, Butterworth, 1959, p. 189.
J. N. Zemel, J. D. Jensen, and R. B. Scholar, *Phys. Rev. A* 140, 330 (1965).
W. W. Scanlon, *J. Phys. Chem. Solids*, 8, 423 (1959).
K. V. Vyatkin and A. P. Shotov, *Sov. Phys. Semicond.* 14, 785 (1980); *Fiz. Tekh. Poluprovodn.* 14, 1331 (1980).
10. Lead Sulfide
G. Guizzetti and A. Borghesi in *HOCS*, 1985, p. 525.
M. Cardona and R. Haensel, *Phys. Rev. B* 1, 2605 (1970).
M. Cardona and D. L. Greenaway, *Phys. Rev. A* 133, 1685 (1964).
M. Cardona, C. M. Penchima, E. E. Koch, and P. Y. Yu, *Phys. Status Solidi B* 53, 327 (1972).
P. R. Wessel, *Phys. Rev.* 153, 836 (1967).
C. E. Rossi and W. Paul, *J. Appl. Phys.* 38, 1803 (1967).
J. N. Zemel, J. D. Jensen, and R. B. Scholar, *Phys. Rev. A* 140, 330 (1965).
11. Lead Telluride
G. Bauer and H. Krenn in *HOCS*, 1985, p. 535.
M. Cardona and R. Haensel, *Phys. Rev. B* 1, 2605 (1970).
M. Cardona and D. L. Greenaway, *Phys. Rev.* 133, A1685 (1964).
D. M. Korn and R. Braunstein, *Phys. Rev. B* 5, 4837 (1972).
W. W. Scanlon, *J. Phys. Chem. Solids* 8, 423 (1959).
J. N. Zemel, J. D. Jensen, and R. B. Scholar, *Phys. Rev. A* 140, A330 (1965).
12. Lithium Fluoride
E. D. Palik and W. R. Hunter in *HOCS*, 1985, p. 675.
B. L. Henke, P. Lee, T. J. Tanaka, R. L. Shimabukuro, and B. K. Fujikawa, *Low Energy X-ray Diagnostics-1981* (D. T. Attwood and B. L. Henke, Eds.), AIP Conf. Proc. No. 75, 1981.
A. P. Lukirskii, E. P. Savinov, O. A. Ershov, and Y. F. Shepelev, *Opt. Spektrosk.* 16, 168 (1964); 16, 310 (1964).
F. C. Brown, C. Gahwiller, A. B. Kunz, and N. O. Lipari, *Phys. Rev. Lett.* 25, 927 (1970).
A. Milgram and M. P. Givens, *Phys. Rev.* 125, 1506 (1962).
T. Tomiki and T. Miyata, *J. Phys. Soc. Jpn.* 27, 658 (1969).
- A. Kachare, G. Andermann, and L. R. Brantley, *J. Phys. Chem. Solids* 33, 467 (1972).
13. Potassium Chloride
E. D. Palik in *HOCS*, 1985, p. 703.
O. Aita, I. Nagakura, and T. Sagawa, *J. Phys. Soc. Jpn.* 30, 1414 (1971).
A. P. Lukirskii, E. P. Savinov, O. A. Ershov, and Y. F. Shepelev, *Opt. Spectrosc.* 16, 168 (1964); *Opt. Spektrosk.* 16, 310 (1964).
T. Tomika, *J. Phys. Soc. Jpn.* 22, 463 (1967).
M. Antinori, A. Balzarotti, and M. Piacentini, *Phys. Rev. B* 7, 1541 (1973).
H. H. Li, *J. Phys. Chem. Ref. Data* 5, 329 (1976).
S. D. Allen and J. A. Harrington, *Appl. Opt.* 17, 1679 (1978).
K. W. Johnson and E. E. Bell, *Phys. Rev.* 139A, 1295 (1965).
14. Silicon Dioxide
H. R. Philipp in *HOCS*, 1985, p. 749.
J. Rife and J. Osantowski, *J. Opt. Soc. Am.* 70, 1513 (1980).
B. L. Henke, P. Lee, T. J. Tanaka, R. L. Shimabukuro, and B. K. Fujikawa, *Low Energy X-ray Diagnostics-1981* (D. T. Attwood and B. L. Henke, Eds.), AIP Conf. Proc. No. 75, 1981.
H. R. Philipp, *Solid State Commun.* 4, 73 (1966); *J. Phys. Chem. Solids*, 32, 1935 (1971).
P. L. Lamy, *Appl. Opt.* 16, 2212 (1977).
H. R. Philipp, *J. Appl. Phys.* 50 1053 (1979).
D. G. Drummond, *Proc. Roy. Soc. London*, 153, 328 (1935).
15. Silicon Monoxide
H. R. Philipp in *HOCS*, 1985, p. 765.
H. R. Philipp, *J. Phys. Chem. Solids*, 32, 1935 (1971).
G. Hass and C. D. Salzberg, *J. Opt. Soc. Am.* 44, 181 (1954).
E. Cremer, T. Kraus, and E. Ritter, *Zs. Electrochem.* 62, 939 (1958).
A. P. Bradford, G. Hass, M. McFarland, and E. Ritter, *Appl. Opt.* 4, 971 (1965).
16. Silicon Nitride
H. R. Philipp in *HOCS*, 1985, p. 771.
H. R. Philipp, *J. Electrochem. Soc.* 120, 295 (1973).
J. B. Theeten, D. E. Aspnes, F. Simonet, M. Errman, and P. C. Mürau, *J. Appl. Phys.* 52, 6788 (1981).
J. Bauer, *Phys. Status Solidi A* 39, 411 (1977).
17. Sodium Chloride
J. E. Eldridge and E. D. Palik in *HOCS*, p. 775.
J. A. Harrington, C. J. Duthler, F. W. Patten, and M. Hass, *Solid State Commun.* 18, 1043 (1976).
T. Miyata and T. Tomiki, *J. Phys. Soc. Jpn.* 24, 1286 (1968); ibid., 22, 209 (1967).
D. M. Roessler and W. C. Walker, *J. Opt. Soc. Am.* 58, 279 (1968).
D. M. Roessler and W. C. Walker, *Phys. Rev.* 166, 599 (1968).
S. Allen and J. A. Harrington, *Appl. Opt.* 17, 1679 (1978).
O. Aita, I. Nagakura, and T. Sagawa, *J. Phys. Soc. Jpn.* 30, 1414 (1971).
18. Zinc Sulfide
E. D. Palik and A. Addamiano in *HOCS*, 1985, p. 597.
B. L. Henke, P. L. Lee, T. J. Tanaka, R. L. Shimabukuro, and B. K. Fujikawa, *Low Energy X-ray Diagnostics-1981* (D. T. Attwood and B. L. Henke, Eds.), AIP Conf. Proc. No. 75, 1981.
M. Cardona and G. Harbecke, *Phys. Rev.* 137, A1467 (1965).
Eastman Kodak, Publ. No. U-72, Rochester, New York (1981).
C. A. Klein and R. N. Donadio, *J. Appl. Phys.* 51, 797 (1980).
T. Deutsch, *Proc. Int. Conf. Phys. Semicond.*, 6th Exeter 1962, p. 505. The Inst. of Physics and the Physical Soc., London, 1962.
A. Manabe, A. Mitsuishi, and H. Yoshinaga, *Jpn. J. Appl. Phys.* 6, 593 (1967).
W. W. Piper, D. T. F. Marple, and P. D. Johnson, *Phys. Rev.* 110, 323 (1958).
19. Polytetrafluoroethylene
J. W. L. Thomas (NIST), Private communication.
NIST Certificate, STM 2044.
P. Y. Barnes, E. A. Early, and A. C. Parr, *NIST Special Publ.* 250-48, NIST Measurement Services: Spectral Reflectance.
Diffuse Reflectance Coatings and Materials Sections, Labsphere Catalog, 1996.
A. Arecchi and C. Ryder (Labsphere, North Sutten, NJ), private communication.